

# NAF™ 15.3mm LAMINATES

30 Year Warranty • AC5 • CARB 2 Certified • 1214mm x 128mm x 15.3mm • 16.73 sf/bx

THICKNESS: 0.60" (15.3 mm)  
 WIDTH: 5" (128 mm)  
 LENGTH: 47.79" (1214 mm)  
 LOCKING SYSTEM: DROP DOWN  
 FINISH: SILK  
 PACKAGE: 16.73 SQFT/BOX  
 48 BOXES/PALLET  
 WEIGHT: 40 LBS/BOX

## COLOURS

- DARK HICKORY
- EXOTIC BIRCH
- GRAPHITE
- GUNSTOCK OAK
- JATOBA
- NATURAL MAPLE
- NATURAL OAK
- RED SANDALWOOD
- SMOKE OAK
- WALNUT OAK

## TECHNICAL

DIMENSION TOLERANCES		
Characteristic	Requirement	Test Method
Squareness	q max. ≤ 0.20mm	EN 13329
Straightness	S max. ≤ 0.30mm/m	EN 13329
Faltness crosswise	F w ,convkav: ≤ 0,15 % F w ,convex: ≤ 0,20 %	EN 13329
Flatness length	F l ,convkav: ≤ 0,50 % F l ,convex: ≤ 1,00 %	EN 13329
Openings between elements	average: ≤ 0,15 mm max.: ≤ 0,20 mm	EN 13329
Height difference between elements	average: ≤ 0,10 mm max.: ≤ 0,15 mm	EN 13329
CLASSIFICATION REQUIREMENTS + LEVEL OF USE + SURFACE TEST		
CLASS	Level of use	Test Method
Abrasion resistance	AC5 (≥ 2000 Umdr.)	EN 13329
Impact resistance	IC1 (≥ 8 N / ≥ 1000 mm)	EN 13329
Effect of a furniture leg	No damage shall be visible when tested with foot type 0	EN 424
Resistance to staining : Groups 1 & 2 Group 3		grade 5 ≥ grade 4
Effect of a castor chair	no change in appearance or damage, as defined in EN 425	EN 425
Thickness swelling	≤ 18 %	EN 13329
Surface soundness	≥ 1,00 N/mm <sup>2</sup>	EN 13329
Light fastness	blue wool scale ,not worse than 6 Grey scale ,not worse than 4	EN 20105-B02 EN 20105-A02
ENVIRONMENTAL CHARACTERISTICS		
Emission of Formaldehyde	CARB2 / Class E1 (≤ 8mg/100g) CARB2 / Class E1 (≤ 0.124mg/m <sup>3</sup> )	EN120 EN 717

