



Accu-Blend Corporation
 364 Malbert Street
 Perris, CA 92570
 Tel: (626) 334-7744
 E-mail: sales@accu-blend.com

ACCU-BLEND WAXES LIST

Accu-Blend Natural Wax

Accu-Blend natural wax line includes: Accu-Soy[®] soy waxes: Accu-Soy 125, Accu-Soy 135, and Accu-Soy 155; Accu-Pure[®] White Beeswax, and Yellow Beeswax. The specifications for each product are listed in the table below.

Natural Wax No.	Melting Point (°F)	Visual Color	Saponification Value	Acid Value
Accu-Soy 125	121-125	White to Off-White	190	26
Accu-Soy 135	131-135	White to Off-White	190	18
Accu-Soy 155	155-160	White to Off-White	180	5
White Beeswax	144 -147	White	87-104	17-24
Yellow Beeswax	144 -147	Yellow	87-104	17-24

Accu-Par[®] Fully Refined Paraffin Wax

Accu-Par[®] paraffin wax line includes: Accu-Par 125, Accu-Par 130, Accu-Par 140, Accu-Par 145, Accu-Par 150, and Accu-Par 160. The specifications for each product are listed in the table below.

Paraffin Waxes Accu-Par No.	Melt Point (°F)	Oil Content (wt%)	Kinematic Viscosity (cSt@210°F)	Needle Penetration (dmm@77°F)	Saybolt Color (White 30 to Yellow -16)
Accu-Par 125	126	0.5	3.3	13	30
Accu-Par 130	130	0.5	3.6	13	30
Accu-Par 140	141	0.5	4.3	11	30
Accu-Par 145	145	0.5	4.5	11	30
Accu-Par 150	149	0.5	4.7	11	30
Accu-Par 160	159	0.5	7.2	11	28

Microlene Microcrystalline Wax

Microlene microcrystalline line includes: Microlene 160, Microlene 165, Microlene 170, Microlene 175, Microlene 185, and Microlene 195. The specifications for each product are listed in the table below.

Microcrystalline Microlene No.	Drop Point (°F)	Oil Content (wt%)	Color (Visual)	Kinematic Viscosity (cSt@210°F)	Needle Penetration (dmm@77°F)
Microlene 160	159	1.0	White	14.1	29
Microlene 165	165	1.0	White	14.3	26
Microlene 170	170	1.0	Amber	14.3	26
Microlene 175	174	1.0	Amber	17.3	16
Microlene 185	185	0.2	Amber	18.0	10
Microlene 195	192	0.2	Amber	18.0	7