



Accu-Blend Corporation
364 Malbert Street
Perris, CA 92570
Tel: (626) 334-7744
E-mail: sales@accu-blend.com



ACCU-SOY #8-CB HYBRID SOY CONTAINER BLEND

Accu-Soy #8-CB Hybrid Soy Container Blend is a combination of soy wax and paraffin wax. It has excellent color retention, jar adhesion, hot and cold scent throw, and is clean burning. No additives are required. It is blended to eliminate frosting of colored candle. It can adhere very well to the glass. Pour with a smooth surface. It has very long burn times.

Physical Properties	ASTM Method	Specifications
Melting Point (°F)	D-87	124
Brookfield Viscosity @190 (°F)	D-445	10 cps
Congearing Point (°F)	D-938	127
Needle Penetration @77 (°F)	D-1321	48 dmm
Color, ASTM	D-1500	L.05
Appearance		Soft, Creamy, Opaque



Out Sanding Features

Accu-Soy #8-CB Hybrid Soy Container Blend has the benefits of the low shrinkage of soy wax combined with the positive scent retention and burning characteristics of paraffin wax. You will get the clean burn of a natural candle and the great scent throw of a paraffin candle. No additives needed, just melt, add color and scent, and then pour.

How to Use

Heat to 160-180 °F degrees, remove from heat source, add fragrance oil and dye, blend and stir while cooling, and then pour at 160 to 180 °F degrees for best results. It is always best to try different temperatures to see what temperature works best for you as there are so many different situations such as glass size, temperature of work area, fragrance percentage, etc..

FDA Status

This product meets USP requirements and FDA requirements for use in non-food articles in contact with food as per 21 CFR 172.880.

Warranty Disclaimer Statement

The information contained in this document is based on tests which are believed to be reliable. As actual conditions of use may vary and are beyond the control of Accu-Blend Corporation, the products specified characteristics cannot be guaranteed and are offered solely for the buyer evaluation and verification. There are no expressed or implied warranties of merchantability or fitness for a particular purpose made by Accu-Blend Corporation, or its directors, officers, employees, or affiliates in connection with the sale of the products.



Accu-Blend Corporation
364 Malbert Street
Perris, CA 92570
Tel: (626) 334-7744
E-mail: sales@accu-blend.com



ACCU-SOY #14-PB HYBRID SOY PILLAR AND VOTIVE BLEND

Accu-Soy #14-PB Hybrid Soy Pillar and Votive Blend is a combination of soy wax and paraffin wax. It has excellent color retention, hot and cold scent throw, and is clean burning. No additives are required. It is blended to eliminate frosting of colored candle. It can release very well from the mold. Pour with a smooth top. It has very long burn times.

Physical Properties	ASTM Method	Specifications
Melting Point (°F)	D-87	142
Brookfield Viscosity @190 (°F)	D-445	10 cps
Congealing Point (°F)	D-938	146
Needle Penetration @77 (°F)	D-1321	19 dmm
Color, ASTM	D-1500	L.05
Appearance		Hard, Opaque



Out Sanding Features

Accu-Soy #14-PB Hybrid Soy Pillar and Votive Blend has the benefits of the low shrinkage of soy wax combined with the positive scent retention and burning characteristics of paraffin wax. You will get the clean burn of a natural candle and the great scent throw of a paraffin candle. No additives needed, just melt, add color and scent, and then pour.

How to Use

Heat to 160-180°F degrees, remove from heat source, add fragrance oil and dye, blend and stir while cooling, and then pour at 160 to 180°F degrees for best results. It is always best to try different temperatures to see what temperature works best for you as there are so many different situations such as glass size, temperature of work area, fragrance percentage, etc..

FDA Status

This product meets USP requirements and FDA requirements for use in non-food articles in contact with food as per 21 CFR 172.880.

Warranty Disclaimer Statement

The information contained in this document is based on tests which are believed to be reliable. As actual conditions of use may vary and are beyond the control of Accu-Blend Corporation, the products specified characteristics cannot be guaranteed and are offered solely for the buyer evaluation and verification. There are no expressed or implied warranties of merchantability or fitness for a particular purpose made by Accu-Blend Corporation, or its directors, officers, employees, or affiliates in connection with the sale of the products.