Technical Data Sheet

| ATP PC/ABS 2000R BK | | | | | | | | | | |
|-------------------------------------------|---------|-------|-------|--------|--|--|--|--|--|--|
| Dog | o vi na | lianı | | | | | | | | |
| Description: PC/ABS Alloy Unfilled Black | | | | | | | | | | |
| Typ | ical A | Annli | icati | ions: | | | | | | |
| ·yp | | тррп | louti | 101101 | | | | | | |
| | | | | | | | | | | |

Mechanical Properties:

| Property | Typical Value | <u>Units</u> | Test Method |
|-------------------------------|---------------|--------------|-------------|
| Specific Gravity | 1.12 | | ASTM-D792 |
| Tensile Strength Break | 6,848 | Psi | ASTM D-638 |
| Flexural Modulus | 313,000 | Psi | ASTM-D-790 |
| Elongation @ Break | 19 | % | ASTM D-638 |
| Izod Impact (23°C, -40°C) | 10 | ft lb/in | ASTM D-256 |
| Melt Flow Rate 230°C | 3.5 | g/10min | ASTM D-1238 |
| Heat Deflection Temp. 264 psi | 208 | °F | ASTM D-648 |

While this information is presented in good faith and believed to be accurate, Arbor Tek Plastics, nor its parent company does not guarantee satisfactory results from reliance upon such information and disclaims all liability for any loss or damage arising out of its use. The above information gives typical properties only. Final determination of the suitability of any information or material for the use contemplated, the manner of use, and whether there is any infringement of patents is the sole responsibility of the user.

Arbor Tek Plastics, Ann Arbor Mi 48108 (734-665-5466) - WWW.ARBORTEK.COM