

NVLAP Bulk Asbestos Proficiency Test
M22024 - December 6, 2024
Individual Laboratory Results

NVLAP Lab Code 200655

Hawaii Analytical Laboratory, LLC
3615 Harding Ave., Suite 308
Honolulu, HI 96816-3759
United States

PROFICIENCY TEST PENALTY POINTS

Sample 1	0
Sample 2	0
Sample 3	0
Sample 4	0
Other *	0
TOTAL POINTS:	0

Failure = 150 or more total points

* Penalty points are assigned for failure to follow instructions. Additional details (if any) for error points assigned are listed below:

Prepared by RTI International for
Participants in NIST's National Voluntary Laboratory Accreditation Program
For Bulk Asbestos Analysis by PLM

NVLAP Bulk Asbestos Proficiency Test
M22024 - December 6, 2024
Individual Laboratory Results

NVLAP Lab Code 200655

Sample 1

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CHRY	Chrysotile	Chrysotile	
% Asbestos (50 pts.)	2	2.4 %	0.1 % to 5.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.551$ $\gamma = 1.556$	$\alpha = 1.552$ $\gamma = 1.558$	α : 1.548 to 1.556 γ : 1.554 to 1.562	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless	
Reporting Additional Asbestos Type (75 pts.)		None	None	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 1: 0

NVLAP Bulk Asbestos Proficiency Test

M22024 - December 6, 2024

Individual Laboratory Results

NVLAP Lab Code 200655

Sample 2 – Type 1

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CHRY	Chrysotile	Chrysotile	
% Asbestos (50 pts.)	4	4.6 %	1.0 % to 8.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.550$ $\gamma = 1.556$	$\alpha = 1.550$ $\gamma = 1.557$	α : 1.546 to 1.554 γ : 1.553 to 1.561	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless	
Reporting Additional Asbestos Type (75 pts.)	ACTN 3 %	N/A	Actinolite / Tremolite	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

NVLAP Bulk Asbestos Proficiency Test

M22024 - December 6, 2024

Individual Laboratory Results

NVLAP Lab Code 200655

Sample 2 – Type 2

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	ACTN	Actinolite	Actinolite / Tremolite	
% Asbestos (50 pts.)	3	2.6 %	0.1 % to 5.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.618$ $\gamma = 1.639$	$\alpha = 1.614$ $\gamma = 1.635$	α : 1.602 to 1.626 γ : 1.623 to 1.647	
Birefringence (10 pts.) *	M	Moderate	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	I	Inclined	Inclined	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless, Green	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 2: 0

NVLAP Bulk Asbestos Proficiency Test

M22024 - December 6, 2024

Individual Laboratory Results

NVLAP Lab Code 200655

Sample 3

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Negative (150 pts.) Asbestos ID error (75 pts.)	CHRY	Chrysotile	Chrysotile	
% Asbestos (50 pts.)	3	3.4 %	0.1 % to 9.0 %	
Refractive Index (40 pts. each index, 10 pts. if $\gamma \leq \alpha$. Max penalty 80 pts.)	$\alpha = 1.549$ $\gamma = 1.558$	$\alpha = 1.549$ $\gamma = 1.556$	α : 1.546 to 1.552 γ : 1.552 to 1.560	
Birefringence (10 pts.) *	L	Low	Low or Moderate *	
Pleochroism (10 pts.)	N	No	No	
Extinction (10 pts.)	P	Parallel	Parallel	
Sign of Elongation (10 pts.)	P	Positive	Positive	
Color (10 pts.)	CL	Colorless	Colorless	
Reporting Additional Asbestos Type (75 pts.)		None	None	

* Birefringence results must be correctly calculated based on participant measured refractive index values.

Total Points Assigned for Sample 3: 0

NVLAP Bulk Asbestos Proficiency Test
M22024 - December 6, 2024
Individual Laboratory Results

NVLAP Lab Code 200655

Sample 4

Criteria	Reported by Laboratory	Mean Reference Values	Acceptable Answers	Assigned Points
Asbestos Type False Pos > 0.1 % (150 pts.) False Pos = 0.1 % (75 pts.)	NONE	None	None	

Total Points Assigned for Sample 4: 0

NVLAP Laboratory Contacts

NVLAP Lab Code 200655

Hawaii Analytical Laboratory, LLC

Please review your contact information below and make sure it is accurate. If there are any changes, please update your information on the RTI website, <https://nvlap-plm.rti.org/>. Also, NVLAP no longer sends the NVLAP Authorized Contact list to RTI at the start of each round. When your NVLAP Authorized Representative changes, please contact NVLAP, nvlap@nist.org, and update your primary contact information on the RTI website.

Laboratory Primary Contact (NVLAP Authorized Contact)

Anne Antin

Email: aantin@analyzehawaii.com

Phone: 808-735-0422

Laboratory / Shipping Contact

Anne Antin

3615 Harding Ave., Suite 308

Honolulu, HI 96816-3759

United States

Email: aantin@analyzehawaii.com

Phone: 808-735-0047

Laboratory Billing Contact

Rozlyn Lubber

Email: rlubber@analyzehawaii.com

Phone: 808-735-0047

Thank you for participating in the NVLAP Bulk (PLM) Proficiency Testing Program.