



## ULTRACRETE-TX1000

All-In-One Multipurpose Texturing Overlay Mix

### PHYSICAL & ARCHITECTURAL STRENGTH PROPERTIES

<b><u>TESTS</u></b>	<b><u>METHOD</u></b>	<b><u>RESULTS</u></b>
Compression Strength	ASTM D695	5450 PSI
Splitting Tensile Strength	ASTM C496	629 PSI
Drying Shrinkage	ASTM C596	No Effect
Direct Tension (Pull Off Method)	ASTM C1583	Stronger than 6000 PSI Concrete (See Photo)



Testing Performed by Western Technologies, Inc., Phoenix, Arizona  
Consulting Engineers and Scientists

ULTRA CONCRETE COATINGS, LLC  
877-485-8721  
[www.ultracrete.com](http://www.ultracrete.com)