



# PVC SDR 17-41 IPS Gasketed



**Specification:** ASTM 2241, NSF 61 Available  
**Compound:** ASTM D1784 Cell Classification 12454  
**Gasket:** ASTM D3139, ASTM F477

White and blue available in color. Available in nominal laying lengths of 20 feet. Pipe is manufactured in a certified ISO 9001:2015 facility using PVC resin manufactured in the US without the use of plasticizers.

PIPE SIZE	AVERAGE O.D.	NOM I.D.	MIN WALL (T)	NOM I.D.	MIN WALL (T)	NOM I.D.	MIN WALL (T)	NOM I.D.	MIN WALL (T)	NOM I.D.	MIN WALL (T)
		PRESSURE CLASS 250 SDR 17 PIPE STIFFNESS: 437 PSI		PRESSURE CLASS 200 SDR 21 PIPE STIFFNESS: 224 PSI		PRESSURE CLASS 160 SDR 26 PIPE STIFFNESS 115 PSI		PRESSURE CLASS 125 SDR 32.5 PIPE STIFFNESS 57 PSI		PRESSURE CLASS 100 SDR 41 PIPE STIFFNESS 28 PSI	
1.5	1.900	1.641	0.112	1.709	0.090	1.745	0.073	1.773	0.060	-	-
2	2.375	2.078	0.140	2.135	0.113	2.182	0.091	2.220	0.073	-	-
2.5	2.875	2.517	0.169	2.585	0.137	2.462	0.110	2.688	0.088	-	-
3	3.500	3.063	0.206	3.146	0.167	3.214	0.135	3.271	0.108	3.320	0.850
4	4.500	3.938	0.265	4.046	0.214	4.133	0.173	4.207	0.138	4.267	0.110
6	6.625	5.803	0.390	5.955	0.316	6.084	0.255	6.193	0.204	6.282	0.162
8	8.625	7.553	0.508	7.754	0.410	7.921	0.332	8.063	0.265	8.180	0.210
10	10.75	9.410	0.632	9.667	0.511	9.874	0.413	10.480	0.331	10.195	0.262
12	12.75	11.160	0.750	11.465	0.606	11.711	0.490	11.919	0.392	12.091	0.311

\* All sizes in inches

