



FLAT GLASS FILM SPECIFICATIONS

On 1/4" Dual Pane Clear Glass

Johnson Window Films' solar control flat glass films on clear glass reject 99% or more of harmful UV rays.

FILM TYPE	COLOR	VISIBLE LIGHT TRANSMISSION	SOLAR ENERGY REJECTION	VISIBLE LIGHT REFLECTANCE		SHADING COEFFICIENT	SOLAR HEAT GAIN COEFFICIENT	U-FACTOR NFRC	SOLAR ABSORPTION	GLARE REDUCTION	FADING REDUCTION	IRED SIRR REJECTION 780-2500 nm		HEAT LOAD REDUCTION RATING
				Exterior	Interior							IRER	SIRR	
1/4" DUAL PANE CLEAR GLASS	clear	78%	30%	14%	14%	0.81	0.70	0.47	28%	0%	0%	37%	51%	not rated

Sunlight.
SPECTRALLY-SELECTIVE CLEAR SOLAR PROTECTION

SUN 70	clear	61%	47%	23%	20%	0.61	0.53	0.46	47%	22%	61%	59%	87%	not rated
---------------	-------	-----	-----	-----	-----	------	------	------	-----	-----	-----	-----	-----	-----------

Palisade.
PREMIUM NANO-CERAMIC SOLAR PROTECTION

PD 50	natural	43%	42%	15%	10%	0.66	0.58	0.47	62%	45%	64%	49%	85%	not rated
PD 45	natural	40%	47%	20%	13%	0.62	0.54	0.47	61%	49%	66%	53%	88%	not rated
PD 40	natural	36%	47%	20%	15%	0.61	0.53	0.48	61%	54%	67%	54%	87%	not rated
PD 75 EXT*	natural	66%	55%	13%	15%	0.52	0.46	0.47	57%	15%	62%	73%	85%	★★★★☆

* Designed for exterior (EXT) use only. This is a spectrally-selective film.

NightScape.
DUAL REFLECTIVE, NON-SPUTTERED FILMS

NS 35	neutral	31%	47%	21%	12%	0.61	0.53	0.47	59%	60%	69%	51%	79%	not rated
NS 25	neutral	23%	57%	36%	17%	0.50	0.43	0.45	57%	71%	73%	60%	86%	★★★★☆
NS 15	neutral	13%	61%	41%	11%	0.44	0.39	0.45	59%	83%	77%	62%	89%	★★★★☆
NS 07	neutral	7%	61%	38%	8%	0.44	0.39	0.45	63%	91%	78%	62%	89%	★★★★☆
NS 05	neutral	5%	55%	17%	12%	0.52	0.45	0.46	73%	94%	77%	60%	88%	★★★★☆

ScenicView.
DUAL REFLECTIVE, NON-FADING FILMS

SV 50	neutral	43%	43%	20%	13%	0.66	0.57	0.48	54%	45%	65%	48%	78%	not rated
SV 35	neutral	32%	51%	28%	18%	0.57	0.49	0.47	58%	59%	69%	56%	87%	★★★★☆
SV 25	neutral	24%	57%	38%	25%	0.49	0.43	0.47	58%	69%	73%	61%	91%	★★★★☆
SV 10	neutral	7%	67%	53%	25%	0.38	0.33	0.47	60%	91%	80%	67%	97%	★★★★★
SV 50 EXT*	neutral	40%	63%	20%	17%	0.43	0.37	0.47	53%	49%	70%	70%	83%	★★★★☆
SV 25 EXT*	neutral	25%	75%	36%	25%	0.29	0.25	0.47	45%	68%	77%	81%	90%	★★★★★
SV 10 EXT*	neutral	8%	88%	56%	26%	0.13	0.12	0.47	37%	90%	85%	91%	97%	★★★★★

* Designed for exterior (EXT) use only.

DaylightNatural.
NEUTRAL, NON-FADING SPUTTERED FILMS

DN 60	neutral	54%	37%	16%	12%	0.73	0.64	0.49	46%	31%	60%	41%	65%	not rated
DN 50	neutral	43%	40%	19%	13%	0.68	0.60	0.49	54%	45%	64%	45%	72%	not rated
DN 35	neutral	32%	44%	22%	17%	0.65	0.56	0.49	57%	59%	68%	46%	74%	not rated
DN 20	neutral	19%	51%	28%	26%	0.57	0.49	0.48	65%	76%	73%	51%	84%	★★★★☆
DN 15	neutral	15%	49%	23%	17%	0.58	0.50	0.48	72%	81%	73%	52%	90%	not rated
DN 35 EXT*	neutral	32%	61%	17%	22%	0.45	0.39	0.47	57%	59%	72%	61%	74%	★★★★☆
DN 20 EXT*	neutral	19%	73%	26%	28%	0.31	0.27	0.47	59%	76%	78%	74%	86%	★★★★★

* Designed for exterior (EXT) use only.

Sunset Bronze.
COPPER, NON-FADING SPUTTERED FILMS

SB 30	bronze	29%	56%	29%	25%	0.51	0.44	0.46	58%	63%	71%	63%	90%	★★★★☆
SB 20	bronze	18%	62%	37%	34%	0.44	0.38	0.46	55%	77%	76%	66%	95%	★★★★★

Solar Silver.
SILVER, NON-FADING METALLIZED FILMS

SS 35	silver	31%	57%	39%	40%	0.49	0.43	0.45	53%	60%	71%	61%	89%	★★★★☆
SS 20	silver	17%	66%	53%	57%	0.39	0.34	0.45	54%	78%	77%	67%	94%	★★★★☆
SS 35 EXT*	silver	31%	73%	41%	36%	0.31	0.27	0.47	37%	60%	75%	80%	89%	★★★★★
SS 20 EXT*	silver	18%	82%	52%	46%	0.21	0.18	0.47	34%	77%	81%	87%	94%	★★★★★

* Designed for exterior (EXT) use only.

Architectural
COLOR METALLIZED SOLAR CONTROL FILMS

MBL 35	blue silver	30%	46%	17%	19%	0.63	0.54	0.47	61%	62%	69%	51%	79%	not rated
MBL 20	blue silver	17%	56%	24%	42%	0.50	0.44	0.45	65%	78%	74%	62%	90%	★★★★☆
MGN 35	green silver	30%	44%	15%	16%	0.64	0.56	0.48	62%	62%	68%	49%	76%	not rated
MGN 20	green silver	17%	55%	22%	41%	0.51	0.45	0.45	67%	78%	74%	62%	89%	★★★★☆
MGD 35	gold silver	29%	57%	35%	40%	0.50	0.43	0.45	56%	63%	72%	61%	88%	★★★★☆
MGD 20	gold silver	15%	65%	47%	57%	0.40	0.35	0.45	58%	81%	77%	67%	94%	★★★★☆

Specialty Series
DECORATIVE SPECIAL APPLICATION FILMS

UV CLR	clear	78%	31%	15%	15%	0.80	0.69	0.48	30%	0%	53%	37%	52%	not rated
WHTFST*	white	61%	38%	23%	23%	0.72	0.62	0.48	38%	22%	59%	42%	61%	not rated
WHTOUT	white	DUE TO LIGHT SCATTERING - NFRC MEASUREMENTS ARE NOT MEANINGFUL												
BLKOUT	black	0%	49%	12%	5%	0.58	0.51	0.48	90%	100%	77%	53%	99%	not rated

* White Frost does not have a recommendation from the Skin Cancer Foundation.



The Skin Cancer Foundation recommends Johnson Window Films products as effective UV protectants.

All Johnson Window Films are protected by CST™ scratch resistant hardcoat.

Solar specifications represent film mounted to 1/4" (6mm) dual pane clear glass.

Tests, equipment and methods according to ASTM, ANSI and NFRC standards. Calculations performed using Lawrence Berkeley Lab's Optics/Window 6. Values expressed hereof are typical and provided for comparative purposes only.

Only the user is aware of the conditions in which the product will be used. It is the user's responsibility to determine if the product is suitable for use.



Johnson Window Films

Manufactured by Johnson Laminating & Coating, Inc.
An ISO 9001:2015 Certified Company

www.johnsonwindowfilms.com



TERMS AND DEFINITIONS

FLAT GLASS FILM SPECIFICATIONS

VISIBLE LIGHT TRANSMISSION

Visible Light Transmission is the percentage of solar visible light (daylight) that passes through a glazing system.

SOLAR ENERGY REJECTED

Solar Energy Rejected is the percentage of total solar energy (heat) that is rejected away from a glazing system. This equals solar heat reflectance plus the amount of solar heat absorbed that is then re-radiated outwards.

EXTERIOR REFLECTANCE

Exterior Reflectance is the percentage of reflectivity (mirror effect) that occurs on the outside of a glazing system. The higher the value, the more reflective the exterior, providing a more mirror-like appearance.

INTERIOR REFLECTANCE

Interior Reflectance is the percentage of reflectivity (mirror effect) that occurs on the inside of a glazing system. The higher the value, the more reflective the interior, providing a more mirror-like appearance.

SHADING COEFFICIENT

Shading Coefficient is the ratio of solar heat gain passing through a glazing system to the solar heat gain that occurs under the same conditions if the window were made of clear, un-shaded double strength window glass (lower SC equals better solar shading performance).

SOLAR HEAT GAIN COEFFICIENT

Solar Heat Gain Coefficient is the percentage of total solar heat that enters a glazing system. This includes heat directly transmitted as well as heat that is absorbed by the glass and then transmitted inwards (lower SHGC means less heat transfer from the exterior to the interior).

U-FACTOR NFRC

U-Factor (or U-Value) is a measurement of solar heat transfer due to outdoor/indoor temperature differences. This represents the amount of heat passing through one square foot of glass in one hour for each 1 degree Fahrenheit temperature difference between the indoor and outdoor. The lower the U-Factor the less solar heat passes through a window of interest for keeping heat inside a building in colder climates.

SOLAR ABSORPTION

Solar Absorption is the percentage of total solar heat that is neither transmitted through nor rejected away from a glazing system (i.e. the percentage of total solar heat absorbed by the glazing system).

GLARE REDUCTION

The ratio of the difference in visible transmission of the glass before and after installing film to the visible transmission of the glass with no film. Expressed as a percentage and is determined by the respective visible transmission values of the glass with and without film.

FADING REDUCTION

Combined fading percentages are determined by applying rejection percentages on each cause of fading to determine the overall reduction in fade that a specific product can return.

Using the IWFA fading explanation found at www.iwfa.com

INFRARED ENERGY REJECTION (IRER)

The measurement of heat experienced from solar infrared radiation (780 - 2,500 nm), which includes both re-radiated and absorbed energy.

SELECTIVE IR REJECTION (SIRR)

Solar infrared radiation (780 - 2,500 nm) not directly transmitted through the glass.

HEAT LOAD REDUCTION RATING

Heat load reduction rating is based on the Solar Heat Gain Coefficient to determine which products offer the most in energy savings.



Johnson Window Films

Manufactured by Johnson Laminating & Coating, Inc.
An ISO 9001:2015 Certified Company

www.johnsonwindowfilms.com