

X-CHEM GLOBAL ORGANIC PIGMENTS

PARTICULAR			APPLICATIONS						PROPERTY			
CI NAME	Mass Tone	Tint Tone	Solvent Base	Water Base	Automotive Refinish	Industrial Paints	Powder Coatings	Coil Coatings	Oil Absorption	Light Fastness Mass Tone/Tint Tone	Weather Fastness Mass Tone	Heat Stability (C)
Pigment Yellow 1			◆	◆	-	-	-	-	40	6-7/4-5	-	160
Pigment Yellow 3			◆	◆	-	-	-	-	35	6-7/4-5	-	160
Pigment Yellow 65			◆	◆	-	-	-	-	45	5-6/4-5	3-4	150
Pigment Yellow 74			◆	◆	-	-	-	-	38	6-7/4-5	3-4	190
Pigment Yellow 83			◆	◆	-	◆	◆	-	50	6-7/5-6	3-4	200
Pigment Yellow 110			-	◆	◆	◆	◆	○	40	7-8/6-7	4-5	200
Pigment Yellow 139			◆	-	◆	◆	◆	-	60	7-8/6-7	4-5	180
Pigment Yellow 151			◆	-	◆	◆	◆	-	80	7-8/6-7	4-5	180
Pigment Yellow 154			◆	◆	◆	◆	◆	-	50	7-8/6-7	4-5	180
Pigment Orange 13			◆	◆	-	◆	-	-	38	5-6/3-4	-	180
Pigment Orange 34			◆	◆	-	◆	◆	-	38	5-6/3-4	-	180
Pigment Orange 36			◆	◆	-	◆	◆	-	45	7-8/6-7	3-4	180
Pigment Orange 64			-	-	-	-	◆	-	45	6-7/5-6	3-4	200
Pigment Red 3			◆	◆	-	-	-	-	45	5-6/3-4	-	160
Pigment Red 4			◆	◆	-	-	-	-	45	5-6/3-4	-	160
Pigment Red 48:1			◆	◆	-	◆	-	-	50	5-6/3-4	-	180
Pigment Red 48:2			◆	◆	-	◆	-	-	50	6-7/4-5	-	180
Pigment Red 48:3			◆	◆	-	◆	-	-	50	6-7/4-5	-	200
Pigment Red 57:1			◆	◆	-	◆	-	-	58	4-5/3-4	-	180
Pigment Red 63:1			◆	◆	-	◆	-	-	55	4-5/3-4	-	160
Pigment Red 112			◆	◆	-	-	-	-	40	6-7/5-6	-	170
Pigment Red 122			-	◆	◆	◆	◆	◆	45	7-8/6-7	4-5	200
Pigment Red 170			◆	◆	-	◆	◆	◆	60	6-7/4-5	3-4	180
Pigment Red 177			-	-	○	◆	◆	◆	70	7-8/6-7	4-5	200
Pigment Red 254			-	-	◆	◆	◆	◆	70	7-8/6-7	4-5	200
Pigment Blue 15:1			◆	◆	-	◆	-	◆	35	7-8/6-7	4-5	200
Pigment Blue 15:2			-	◆	◆	◆	-	◆	35	7-8/6-7	4-5	200
Pigment Blue 15:3			◆	◆	◆	◆	-	◆	45	7-8/6-7	4-5	200
Pigment Blue 15:4			◆	◆	◆	◆	-	◆	40	7-8/6-7	4-5	200
Pigment Green 7			◆	◆	◆	◆	◆	◆	40	7-8/6-7	4-5	200
Pigment Violet 19			◆	◆	◆	◆	◆	◆	50	7-8/6-7	4-5	200
Pigment Violet 23			◆	◆	○	◆	◆	◆	45	7-8/6-7	4-5	250

Recommended	◆
Partial Recommended	○
Not Recommended	-

