



OR 60BM

Product Description

- 100% solids, two-component pure polyurea
- Contains no VOC's
- Good resistance to inorganic bases, acids and hydrocarbon solvents
- Fair resistance to oxygenated and chlorinated solvent
- Good resistance to hot water up to 180° F

Primary Applications

- Hand mix/batch material
- Use as a non-immersion grade tank lining for steel and concrete tanks
- Lining of material handling equipment
- Coating of urethane or expanded polystyrene foam insulation
- Waterproofing of structures
- Protection of concrete from acid and alkaline materials
- Use as an environmental containment barrier with or without geotextiles
- Used for lining interior of truck beds
- Use as tank lining material

Color

Standard color is black. Contact SplatSeal Ltd for additional color options

Storage

12 months in unopened containers at 50-90° F

Typical Physical Properties

Tensile Strength	ASTM-D412	2800
Elongation (%)	ASTM-D412	225%
Tear Strength (PLI)	ASTM-D624	350
Hardness (shore D)	ASTM-D2240	60
Abrasion resistance	Excellent	
Viscosity B side	CPS	500-600
Viscosity A side	CPS	500-600
Ratio A/B	1:2	
Density B side	1.025	
Density A side	1.14	
Flash point	ASTM-D56	>720° F
VOC Testing	CAN/ULC-S774	P >200° F
Weight	8.5 lbs./gallon	
Gel Time	25 to 30 minutes	
Tack Free Time	about 1 hour	
Foot traffic	4 hours	
DFT coverage	40 mils	40 sq. ft/gal

Coverage

80 Sq. Ft. per gallon @20 Mils

Primer

OR 711, OR PR811, OR E41, Wet/green concrete OR T11

Toxicity

Iso component contains polymeric isocyanate fresh air supply-respirator
Use gloves and protective clothing during application

Application:

Surface Preparation: general: surface must be properly prepared prior to

application. This could entail shot blasting or grinding, scrubbing, high pressure detergent washing, steam cleaning or solvent wiping of the surface to remove dirt, oil, grease pollutants and other contaminants. Allow the surface to thoroughly dry. Once dry, remove loose or excess mortar or other material that may work to impair adhesion.

Density

Part A	9.2lbs/gallon
Part B	7.4lbs/gallon

Materials needed to mix: 2 ½ gal or 5-gallon pail, electric drill and spiral mixer.

Mixing/Stirring:

1. Pour part "A" into a clean pail
2. Pour part "B" into the same pail with the part "A"
3. Mix thoroughly
4. **Very Important** - Mix "B" into "A" in **small quantities** slowly. Product has approximate ½ hour working time

Application: Material can be applied by brush, roller, squeegee or low pressure spray equipment. Ensure product is applied in an even and uniform manner, making sure recesses and edges are thoroughly coated.

Handling and storage: The reaction of isocyanates Part A with water leads to the formation of insoluble urea's and carbon dioxide gas, which gas become contaminated with moisture should not be subsequently sealed; otherwise a hazardous increase in pressure may result.

OR 60BM: Resistant to short-term exposure to low temperatures. However, low temperatures will result in increased viscosity, which makes handling more difficult. It is not advisable to store OR60BM for long periods below 32°F (0°C). The recommended storage temperature for OR 60BM is 50° -90°F. A small number of insoluble solids in the A-side liquid product does not usually cause difficulties in handling or product performance. However, if necessary, the liquid product may be filtered through a suitable in-line filter.

Warranty

The technical data and any other printed information furnished by SplatSeal are true and accurate to the best of our knowledge. OR 60BM conforms to in house quality control procedures and should be considered free of defects. The data provided is believed to be reliable and is offered solely for evaluation. The use of this product is beyond the control of the seller therefore the buyer assumes all risks of use and handling whether done in a matter that is in accordance with the provided posted directions or not. SplatSeal makes no warranty; expressed or implied, of its products and shall not be liable for indirect or consequential damage in any event.

Sales and Customer Support 720-275-7511

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. SPLATSEAL LTD WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY. THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN, EXPRESSED OR IMPLIED WARRANTIES

Distributor of SplatSeal Polyurea

720-275-7511

1800 Commerce Street Ste A, Boulder, CO 80301 www.splatseal.com



OR 60BM

SPLATSEAL LTD EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT, ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. SPLATSEAL LTD REQUIRES APPLICATORS TO BE CERTIFIED THROUGH ATTENDING A ONE- OR TWO-DAY TRAINING SESSION HELD AT OUR BOULDER, CO FACILITY TO SPRAY OR PRODUCTS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE SPLATSEAL LTD OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF. 11/21

Disclaimer

The technical data and any other printed information furnished by SplatSeal Ltd. (SSL) are true and accurate to the best of our knowledge. SSL products conform to in house quality control procedures, tested and should be considered free of defects. The data provided is believed to be reliable and is offered solely for evaluation. The use of the product is beyond the control of the seller; therefore, the buyer assumes all risk whatsoever as to the use of these materials and handling whether done in a matter that is in accordance with the provided posted directions or not. Failure to strictly adhere to recommended procedures and attend a one-day Certified Applicator training, held at the corporate facility located in Boulder, CO for proper application of SSL products and materials, shall relieve SSL of all liability with respect to the materials or the use thereof. This buyer sole and exclusive remedy. All claims concerning product defects must be made in writing within (6) six months of shipment. The absence of such claims in writing during this period will constitute a wave of all claims with respect to such product. This warranty shall be in lieu of any other warranty, expressed, or implied, including, but not limited to any warranty of merchantability or fitness for a particular purpose. 12/20

Distributor of SplatSeal Polyurea

720-275-7511

1800 Commerce Street Ste A, Boulder, CO 80301 www.splatseal.com