

	PROPERTY		UNIT	METHOD	MIN	MAX	TYPICAL
	Density at 15°C		g/ml	ASTM D 1298		0,88	0,823
	Astm Colour		-	ASTM D 1500	-	0,5	0,5
	Saybolt Color				30	-	31
	Viscosity at 100°C		cSt	ASTM D 445	2,7	3,3	2,8
	Viscosity at 40°C		cSt	ASTM D 445			10
	Viscosityindex		-	ASTM D 2270	100	-	
	Flash point °C		°C	ASTM D 92		-	180
	Pourpoint		°C	ASTM D 97	-40	-9	-42
	Ramsbottom CarbonResidue		wt %	ASTM D 524	-	-	0,06
	Sulfur		wt %	ASTM D 4294	-	0,001	
	AcidNumber		mg KOH/g	ASTM D 664	-	0,01	-