

Technical Data Sheet of Oxidized Bitumen 150/5

Bitumen 150/5	Test method	Unit	Specification
Specific gravity @25/25 C	ASTM D70	(Kg/m3)	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	4/6
Softening point °C	ASTM D36	°C	145/155
Ductility @25 °C	ASTM D113	Cm	1.5min
Loss on heating(wt) %	ASTM D6	Wt. %	0.2 max
Flashpoint °C	ASTM D92	°C	250 min
Solubility in CS2(wt) %	ASTM D4	Wt. %	99.5 max
Spot test	A.A.S.H.O.T102	—	Negative

bitumen 150/5, blown asphalt 150/5, blown bitumen 150/5, Hard Grade Asphalt, Hard Grade Bitumen, hard grade bitumen 150/5, Iran blown asphalt, Iran Blown Asphalt Manufacturer, Iran blown asphalt supplier, Iran blown bitumen, Iran blown bitumen manufacturer, Iran Blown bitumen supplier, Iran oxidized bitumen, Iran oxidized bitumen manufacturer, Iran oxidized bitumen supplier, oxidized asphalt 150/5, oxidized bitumen 150/5