






	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		

Description

U500 Single Stage is two-component polyurethane designed for original equipment and repairs for commercial vehicles. U500 Single Stage is a cost-effective durable finish with good color capability that is simple to mix and easy to apply. U500 Single Stage is HAPs compliant with a ready to spray VOC less than 5.0 lbs/gal.

	Safety Considerations Use suitable personal protection. AkzoNobel recommends the use of a fresh air supply respirator. Refer to the product Safety Data Sheet (SDS) for more complete safety information.																		
 Stick #106	Mixing 3 1	Parts by volume U500 Single Stage ready mix color Parts by volume U500 Hardener																	
	Spray-Gun Set-Up: <table border="1" data-bbox="313 827 1419 957"> <tr> <td>RP – Pressure Feed</td> <td>0.8 – 1.4mm</td> <td>30 – 36psi</td> <td>12 – 16 oz/min</td> </tr> <tr> <td>RP – Gravity Feed</td> <td>1.2 – 1.4mm</td> <td>30 – 35psi</td> <td></td> </tr> <tr> <td>HVLP – Pressure Feed</td> <td>1.0 – 1.2mm</td> <td>Max 10psi (cap)</td> <td>12 – 16 oz/min</td> </tr> <tr> <td>HVLP – Gravity Feed</td> <td>1.4 – 1.5mm</td> <td>Max 10psi (cap)</td> <td></td> </tr> </table>			RP – Pressure Feed	0.8 – 1.4mm	30 – 36psi	12 – 16 oz/min	RP – Gravity Feed	1.2 – 1.4mm	30 – 35psi		HVLP – Pressure Feed	1.0 – 1.2mm	Max 10psi (cap)	12 – 16 oz/min	HVLP – Gravity Feed	1.4 – 1.5mm	Max 10psi (cap)	
RP – Pressure Feed	0.8 – 1.4mm	30 – 36psi	12 – 16 oz/min																
RP – Gravity Feed	1.2 – 1.4mm	30 – 35psi																	
HVLP – Pressure Feed	1.0 – 1.2mm	Max 10psi (cap)	12 – 16 oz/min																
HVLP – Gravity Feed	1.4 – 1.5mm	Max 10psi (cap)																	
	Application Apply two to three single flowing coats.																		
	Flash Between Coats at 70°F (21°C) 10-15 minutes	Flash Before Force Drying at 70°F (21°C) 5-10 minutes																	
	Drying <table border="1" data-bbox="313 1320 899 1421"> <tr> <td></td> <td>70°F (21°C)</td> <td>140°F (60°C)</td> </tr> <tr> <td>Dust Free</td> <td>35 min</td> <td>N.A.</td> </tr> <tr> <td>Dry to handle</td> <td>12 hrs</td> <td>45 min</td> </tr> </table>				70°F (21°C)	140°F (60°C)	Dust Free	35 min	N.A.	Dry to handle	12 hrs	45 min							
	70°F (21°C)	140°F (60°C)																	
Dust Free	35 min	N.A.																	
Dry to handle	12 hrs	45 min																	

Read complete TDS for detailed product information.

	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		

Description

U500 Single Stage is two-component polyurethane designed for original equipment and repairs for commercial vehicles. U500 Single Stage is a cost-effective durable finish with good color capability that is simple to mix and easy to apply. U500 Single Stage is HAPs compliant with a ready to spray VOC less than 5.0 lbs/gal.

Suitable Substrates


<ul style="list-style-type: none"> · Existing finishes, degreased and sanded with #P320 to #P400 grit paper dry. · 2K Surfacer · 2K100 Surfacer · 460 Tintable Sealer · 460 Flex Tintable Sealer 	<ul style="list-style-type: none"> · E250 Epoxy Primer · E350 Epoxy Primer · E380/E381 Epoxy Primer · Plastic Adhesion Promoter
---	---

Products and Additives

Product	U500 Single Stage Intermix Tints	Item # Please reference price list
Hardeners	U500 Hardener	Item #484507 (Quart) Item #483668 (Gallon) Item #518451 (5 Gallon) Item #516071 (53 Gallon)
Reducer	U99 Reducer Added to color mix automatically in MixIt	Item #483664 (Gallon) Item #484506 (5 Gallon)
Additives	998 Accelerator – Accelerate dry times 997 Enhancer – Potlife extender that slows flash off, allows for better melt in at high temperatures LV Flex – For flexible substrate application F100 Flattening Agent – Low gloss additive B91 Reducer SRA B92 Reducer LV SRA	Item #483670 (250 mL) Item #398679 (Pint) Item #398767 (Quart) Item #483673 (Gallon) Item #510324 (Quart) Item #509407 (Quart)

Basic Raw Materials


- U500 Single Stage – Polyol resins
- U500 Hardener – Polyisocyanate resins
- U99 Reducer – solvent blend
- Additives- Refer to the individual TDS for information.

	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		

Product Characteristics

- Weight per gallon (Ready mix color): 8.0-9.2 lbs/gal
- Volume Solids (Ready to mix color): 40% +/- 2%
- Gloss – High
- Color – Solid, metallic and pearl


Product Agitation

	<p>Stirring</p> <ul style="list-style-type: none"> • Because U-TECH U500 is a high solids product it needs to be thoroughly agitated before use. • Stir the several times per day.
---	---


Mixing Colors


	<p>Formulas</p> <ul style="list-style-type: none"> • A wide range of formulas are available to match the most popular colors. These are available in MixitPro. <p>Hand Mixing Colors</p> <ul style="list-style-type: none"> • Colors can be custom mixed.
--	---

Mixing – High Gloss

 <p>#106 Stick</p>	<p>3 1</p>	<p>Parts by volume U500 Single Stage RM Parts by volume U500 Hardener</p> <p>Add up to 1 ounce of 998 Accelerator per RTS gallon to speed up cure.</p>
--	------------------------------	--


Mixing – Low Gloss

 <p>#107 Stick</p>	<p>5 1</p>	<p>Mix 100 parts by weight of ready mix color (including the U99 Reducer) with F100 Flattening Agent according to the table below.</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th>Gloss Range</th> <th>Amount of RM Color by weight</th> <th>Amount of F100 by weight</th> </tr> </thead> <tbody> <tr> <td>Antique (70 – 80)</td> <td style="text-align: center;">100</td> <td style="text-align: center;">10 – 30</td> </tr> <tr> <td>Eggshell (50 – 60)</td> <td style="text-align: center;">100</td> <td style="text-align: center;">40 – 60</td> </tr> <tr> <td>Semi-gloss (40 – 50)</td> <td style="text-align: center;">100</td> <td style="text-align: center;">60 – 80</td> </tr> <tr> <td>Matte (20 – 30)</td> <td style="text-align: center;">100</td> <td style="text-align: center;">110 – 150</td> </tr> <tr> <td>Flat (10 - 20)</td> <td style="text-align: center;">100</td> <td style="text-align: center;">150 - 220</td> </tr> </tbody> </table> <p>High amounts of F100 Flattening Agent may cause a drop in coverage. Amount of F100 may vary from color to color.</p> <p>Parts by volume U500 Single Stage RM with F100 Flattening Agent Parts by volume U500 Hardener</p>	Gloss Range	Amount of RM Color by weight	Amount of F100 by weight	Antique (70 – 80)	100	10 – 30	Eggshell (50 – 60)	100	40 – 60	Semi-gloss (40 – 50)	100	60 – 80	Matte (20 – 30)	100	110 – 150	Flat (10 - 20)	100	150 - 220
Gloss Range	Amount of RM Color by weight	Amount of F100 by weight																		
Antique (70 – 80)	100	10 – 30																		
Eggshell (50 – 60)	100	40 – 60																		
Semi-gloss (40 – 50)	100	60 – 80																		
Matte (20 – 30)	100	110 – 150																		
Flat (10 - 20)	100	150 - 220																		



	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		

Mixing – Flexible Parts

If the part to be painted can be deformed by hand, increase the flexibility of U500 Single Stage as follows.

	100 15	When spraying U500 over flexible substrates that have been primed with a U-TECH primer that has been flexed, use the following ratio by volume.
		Parts by volume U500 Single Stage RM Parts by volume LV Flex Additive

Stir the paint with Elast-O-Actif together THEN –

	3 1	Parts by volume U500 Single Stage RM Flexed
		Parts by volume U500 Hardener
		


Viscosity When Mixed


	25-35 seconds	Measured with a DIN #4 viscosity cup at 70°F (21°C).

Pot-Life When Mixed


Product Mix	70°F (21°C)
U500 Single Stage RM ready to spray	4 hours
U500 Single Stage RM ready to spray with 998 Accelerator	1 hour
U500 Single Stage RM ready to spray with 997 Enhancer	5 hours

Spray Gun Set-Up


	Consult spray gun manufactures instructions for specific spray gun pressure specifications.			
	Spray Gun	Fluid Tip	Application Pressure	
	RP – Pressure Feed	0.8 – 1.4mm	30 – 36psi	12 – 16 oz/min
	RP – Gravity Feed	1.2 – 1.4mm	30 – 35psi	
	HVLP – Pressure Feed	1.0 – 1.2mm	Max 10psi (cap)	12 – 16 oz/min
	HVLP – Gravity Feed	1.4 – 1.5mm	Max 10psi (cap)	

	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		



Application


	<p>Solids Apply two (2) to three (3) single flowing coats. Follow recommended flash time between coats.</p> <p>Metallics Apply two single flowing coats. Follow the recommended flash time between coats. Each coat of U500 Single Stage should be applied with sufficient flow, but should not be applied too heavily or excessive mottling will occur. Once hiding has been achieved an orientation coat may be applied if required. Allow a short flash of 5 - 10 minutes @ 70°F (21°C) then even out the metallic pattern with a final mist coat by lowering air pressure 3 - 5 psi and hold the spray gun at a 45° angle to the panel with increased distance of about 10 - 15 inches. Adjust the material flow from the spray gun by means of trigger control. Do not make this coat too wet. A light mist coat lightens the color. A heavy or wet mist coat will make the color darker. Proper application greatly affects the final color appearance.</p> <p>Note: U500 Single Stage will continue to flow and level during flash and bake.</p>
---	---

Clearcoat Options

	<p>Integrated Clearcoat (solid colors only) Apply two (2) to three (3) coats of U500 Single Stage for coverage. Allow single stage to flash 10 – 15 minutes. Activate MS Clearcoat (see MS Clearcoat TDS). Then integrate RTS MS Clearcoat with U500 Single Stage RM color 1:1 by volume. Apply final wet coat.</p> <p>Clearcoat For added durability one (1) wet coat of MS Clear may be applied over U500 Single Stage. Allow single stage to flash for at least one hour prior to clear coating. Recommend using 998 accelerator in U500 Single Stage when clear coating.</p>
---	--

Spot Repairs using B91 SRA Reducer or B92 LV SRA Reducer

	<p>Mixing Single Stage: 100 parts by volume U500 Single Stage ready to spray 200 parts by volume B91 or B92 SRA Reducer</p> <p>Clearcoats: 100 parts by volume U-TECH 4.0 or MS Clearcoat ready to spray 50 parts by volume B91 or B92 SRA Reducer</p>
	<p>Application Method</p> <ol style="list-style-type: none"> 1. Apply one thin coat of the overspray edge. 2. Allow a flash time of 10-15 seconds. 3. Apply pure B91 or B92 SRA Reducer to overspray edge. 4. Allow a flash time of 10-15 seconds. 5. Apply an additional thin coat of B91 or B92 SRA Reducer if necessary. 6. Allow to dry and polish.


	North America	Technical Data Sheet	
	U500 Single Stage	Topcoat	
		9/1/2016	
FOR PROFESSIONAL USE ONLY			

Film Thickness – Using Suitable Application

2 Coats will achieve a thickness of 1.8-2.2 mils (45 – 55µm).


Drying / Curing Time

Drying times are stated a recommended application method, film thickness and object temperature.


		U500 Single Stage		1 oz 998 Accelerator per RTS Gallon		2 oz 997 Enhancer per RTS Gallon	
		70°F (21°C)	140°F (60°C)	70°F (21°C)	140°F (60°C)	70°F (21°C)	140°F (60°C)
		Dust Free	35 minutes	NA	20 minutes	NA	45 minutes
Dry to Handle	12 hours	45 minutes	80 minutes	35 minutes	12 hours	55 minutes	

Note: 998 will decrease Potlife. Extreme temperatures may require higher amounts of 997.


Recoating

	U500 Single Stage can be recoated with itself at any stage or clear coated after 1 hour flash at 70°F (21°C). Sanding is necessary after 24 hours.
--	--

Polishability


	<p>Dust and minor damage can be polished out after recommended dry times. If baking, allow a cool down period of the object to ambient temperature.</p> <ul style="list-style-type: none"> - Carefully de-nib out dust particles with #1500 then #2000 grit paper. Clean and dry the surface - Mechanically polish area using quality rubbing compounds followed by polishing glaze - For extensive color sanding and buffing of solid colors, it is necessary to apply one (1) or two (2) MS Clear
---	--

Cleaning of Equipment

	Clean equipment with extra strong cleaning solvents.
---	--

Theoretical Coverage

	<p>Theoretical coverage is dependent of many factors. These may include; the shape of the object, surface smoothness, application technique and other application variables among others.</p> <ul style="list-style-type: none"> · 642 Sq ft / gallon · 15.7 M² / liter
--	--

	North America	Technical Data Sheet
	U500 Single Stage	Topcoat
		9/1/2016
FOR PROFESSIONAL USE ONLY		

VOC / Regulatory Information

U500 Single Stage RM ready to spray at 3:1 mix ratio – <5.0 lbs/gal (<600 g/L)
--

Product Storage

	Stock unopened or used products in approved closed containers with proper labeling. Store in moderate temperatures between 40°F - 95°F (5°C – 35°C). Avoid too much temperature fluctuation. Optimum storage temperature is approximately 70°F (21°C).	
	Intermix Tints	2 years
	U500 Binder	1 year
	U500 Hardener	1 year
	998 Accelerator	1 year
	997 Enhancer	1 year
	LV Flex Additive	1 year
	F100 Flattening Agent	2 years
	B91 SRA Reducer	2 years
	B92 LV SRA Reducer	2 years

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel.

AkzoNobel 1845 Maxwell Street Troy, MI 48084 USA 1-800-618-1010