

Distributed exclusively in North America by:

US Chemical & Plastics

A Division of Alco Industries Inc.

600 Nova Drive S.E., Massillon, Ohio 44646

330-830-6000

www.uschem.com

1K Self Etch Primer

Prod.no. 3 680 003 grey

TECHNOLOGY

SprayMax®



Aerosol formulation made for this specific product for easy application
constant atomization pressure
finest aerosol distribution,
professional paint result

PRODUCT

1K etch primer, welding primer; welding certificate, chromate-free, easy and quick application, excellent corrosion protection, even application, smooth flow, also wet-in-wet application possible, rapid drying

Basis of raw material:

Polyvinyl butyral, contains phosphoric acid

VOC value

3.6 lbs/gal (415 g/l)

FIELD OF APPLICATION

Recommended for:

Spot Repair and parts refinishing, especially for sand-through areas
welding primer, rust protection primer, filler primer

Substrate:

bare metal, sanded;
fully hardened paint coats, sanded,
priming of spare parts, sanded;
polyester surfaces, sanded
aluminium, sanded
zinc-coated metals (3-coat process)
GRP (glass-fibre reinforced plastic)

Pre-Treatment:



remove any rust if required, sand surface, clean surface carefully with SprayMax® SILICONE REMOVER, product no. 3 680 090; area must be free from grease, dust and humidity. Shake aerosol vigorously for 2 min, spray to test.

PROCESSING:

Protections:



personal protection is required
respirator mask type A2/P2



protective gloves,
e.g. from latex or nitrile

Spray passes



welding primer: 1 = 0.2 – 0.4 mil
(6 – 10 µm)

primer: 1 – 2 = 0.6 – 1.2 mil
(15 – 30 µm)

filler primer: 2 – 3 = 1.2 – 2.0 mil
(30 – 50 µm)

Drying:



primer and
welding primer: 10 – 15 min /70 °F (20 °C)

filler primer: 15 – 60 min /70 °F (20 °C),
depending on coat thickness



IR drying possible
7 min (short-wave drying)

Continue:


wet sanding with P 800 or dry scuff sanding with
P 400 – 500;
wet-in-wet application possible after 15 – 30 min
flash-off time;

Can be coated with any commercial filler and
topcoat.

Do not coat with polyester and EP products.

SprayMax® 1K FILLER PRIMER has a 3 months
weathering resistance on steel stored in the open
air. Hereby the dried coat thickness should not be
less than 2.0 mil (50 µm).

Finish:



When work is finished, reverse aerosol and spray
valve empty.

Disposal:

The emptied aerosols are suitable for household
collection.



CHARACTERISTICS

Solid content:	23.6 % per weight
Coverage:	approx. 775 – 1163 sq inch (0.5 - 0.75 m ²)/ aerosol at approx. 1.2 – 1.6 mil (30 – 40 µm) dried film thickness
Gloss degree	n.a.
Shelf life:	36 months /70 °F (20 °C)
Remarks:	For professional use only

SprayMax® is a registered trade mark of the Peter Kwasny Group.
The information contained in this paper corresponds to our present knowledge and is a guide to our products and their uses. It is not to be understood as a guarantee for certain properties of our products or of their specific applications. The warnings printed on our labels must be respected. Any industrial property rights should be observed.