

U-POL®

HS GRAVITEX PLUS STONE CHIP PROTECTOR

Description

GRAVITEX PLUS is a tough, hard, durable coating designed to reproduce the manufacturers original stone chip finish. It will protect against stone chips, salt, damp and rust. **GRAVITEX PLUS** will also help to deaden sound and vibrations and is, therefore, ideal for application to panels and inside engine compartments. The high build formula will cover weld marks and seams, often in one application.

Health & Safety Statement

FOR PROFESSIONAL USE ONLY. Read full instructions before use.

IMPORTANT: This product contains hazardous materials and therefore appropriate personal protective equipment should always be used. Please refer to the label and consult the material safety data sheet for full handling instructions and personal protection information. These are available via your local stockist or via the U-POL website at WWW.U-POL.COM.

U-POL disclaim any liability where the user does not wear the recommended personal protective equipment.

Surface Preparation & Instructions for Use

GRAVITEX PLUS stone chip protector can be used on the following surfaces:-

- Suitably prepared bare metal. For overcoating aluminium, **ACID #8** etch primer is recommended.
- Original paint surfaces (with the exception of thermoplastic acrylics).

Thoroughly clean and degrease old paint surfaces with a suitable spirit wipe or thinner. Wet flat with 400 grade paper. For bare metal use 180 grade paper. Re-clean and dry.

Application

Shake the tin before use. Apply with a clean Schutz gun or brush. Allow approximately 10-15 mins. for the solvent to flash off when building a thick coat.

Thinners

GRAVITEX PLUS is supplied ready for use.

Build & Pressure

One coat of **GRAVITEX PLUS** will give a build of approximately 100-150 microns and a pressure of between 2.76 - 4.82 BAR is required at the gun. Less or more pressure will give a flatter or more rippled effect.

Drying Time

Approximately 2 hours at normal shop temperature or 30 mins. at low bake (80°C). Drying time is dependent on film thickness, humidity and temperature.

Over-Painting

GRAVITEX PLUS may be over-painted with most paint systems. With 2 pack acrylic paints its can be over-painted wet on wet. For optimum gloss and protection from fading, the use of a U.V Clear is recommended.

U-POL®

VOC Information

	As Packaged UP0721 & UP0792		As Packaged UP0722		As Packaged UP0723 & UP0793	
VOC Regulatory	432g/l	3.6lbs/gal	424g/l	3.5lbs/gal	432g/l	3.6lbs/gal
VOC Actual	423g/l	3.5lbs/gal	424g/l	3.5lbs/gal	430g/l	3.6lbs/gal
Volatiles	44.85% by weight		41.06% by weight		42.64% by weight	
Water	0% by weight	0% by volume	0% by weight	0% by volume	0% by weight	0% by volume
Exempt Compounds	2.7% by weight	2.09% by volume	0.00% by weight	0.00% by volume	0.50% by weight	0.38% by volume
Density	1005g/l	8.4lbs/gal	1034g/l	8.6lbs/gal	1021g/l	8.5lbs/gal

Product Codes

- UP0721 - Black Color/ 1L tin.
- UP0722 - White Color/ 1L tin.
- UP0723 - Gray Color/ 1L tin.
- UP0792 - Black Color / 25L drum.
- UP0793 - Gray Color / 25L drum

U-POL US, Inc., 630 Selvaggio Dr, Suite 300, Nazareth, PA 18064
 Tel: (800) 340 7824; Fax: (800) 787 5150
 Email: sales-us@u-pol.com Website: www.u-pol.com