

December 16, 2016

Legacy Safety & SECURITY 125 Stafford Place New Orleans LA 70124 Attn: Robert Hausman

Dear Mr. Hausman:

In accordance with your instructions, Oregon Ballistic Laboratories conducted stab testing on one sample.

The sample were tested in accordance with NIJ-0115.0 in an indoor lab. Two laser break screens, in conjunction with one time-based frequency counter, were used to measure impact velocity and calculate strike energy. Penetrations were determined by examination of NIJ foam and polyart paper.

Samples will be maintained at Oregon Ballistic Laboratories for 30 days and then discarded, unless other instructions are received. If you have any further questions or concerns, please contact us.

Sincerely,

Brandon Bertsch

Oregon Ballistic Laboratories

B-13 H



STAB RESISTANCE TEST

Customer: Legacy Safety & SECURITY OBL ID#: 12206

Test Date: 3/8/2016 Purchase Order:

TEST SAMPLE
Sample No.: LTFDNIJ2012-01-3a
Serial No.: N/A

N/A N/A Lot No.: Plies: Description: N/A N/A Size (in.): Weight (lb.): Thickness: Avg. Thk. (in):

10x12 1.70 0.857 0.863

0.861 0.862

0.871

RANGE SET-UP

Frequency counter (HP 5316B) NIJ Foam Velocity measurement: Witness Material: Armor Condition: Ball Drop Bounces (in.): New 15.5 & 15.5

Tester:

Recorder: Temperature: Rel. Humidity:

Justin Greely Justin Greely 69.4 40.3

Bar. Pressure: 29.97

STANDARDS / PROCEDURES NIJ-0115.0

IMPACT NO.	THREAT	TIP SHARPNESS (HRC)	LEVEL	ENERGY LEVEL	Drop Mass (kg.)	ANGLE OF INCIDENCE (DEGREES)	DROP HEIGHT (M)	TIME ms (10-3)	IMPACT VELOCITY (M/S)	STRIKE ENERGY (J)	DEPTH OF PENETRATION (MM)	NOTES
1	P1	-53	1	E1	1.910	0°	1.315	8.089	5.02	24.11	6.54	Max Penetration: 7 mm
2	P1	-72	1	E2	1.910	0°	2.032	6.625	6.13	35.93	19.10	Max Penetration: 20 mm
3	S 1	-71	1	E1	1.920	0°	1.314	8.105	5.01	24.14	2.88	
4	S 1	-85	1	E2	1.920	0°	2.037	6.556	6.20	36.89	6.63	
5	P1	-84	1	E1	1.910	45°	1.317	8.148	4.99	23.76	6.26	
6	S1	-106	1	E1	1.920	45°	1.315	8.108	5.01	24.12	0.53	

REMARKS: Spike weight = 1.910kg Blade weight = 1.920kg

TEST RESULTS: Passed.