



Client: DIXON SAND (PENRITH) PTY LTD

PO BOX 148

PENRITH NSW 2751

Job No 7555/1 Date Tested: 04/08/2022

Tested By: NP Checked By: AK

Project: MATERIAL ANALYSIS

MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)		
Material Description	Fine SAND	
Sieve Analysis		
Laboratory Number	7555/1-490	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	
4.75mm	100	
2.36mm	100	
1.18mm	94	
600 microns	75	
300 microns	29	
150 microns	7	
75 microns	3.5	
Date Sampled	July 2022	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Accredited for compliance with ISO/IEC 17025.

A Kench

05/08/2022

Approved Signatory

Nata Accreditation Number 2734 Corporate Site Number 2727

Head Office:

34 Borec Road, Penrith NSW 2750 P O Box 880 Penrith NSW 2751

Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:

Unit 4, 18-20 Whyalla Place, Prestons NSW 2170 Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au