

Client: DIXON SAND (PENRITH) PTY LTD  
PO BOX 148  
PENRITH NSW 2751

Job No 7555/1  
Date: 07/06/2023  
Tested By: TS  
Checked By: AK

Project: MATERIAL ANALYSIS  
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

## TEST RESULTS

Page 1 of 1

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (Yellow)	
Sieve Analysis		
Laboratory Number	7555/1-529	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing
4.75mm	100	
2.36mm	93	11.6
1.18mm	77	
600 microns	49	
300 microns	15	
150 microns	3	
75 microns	0.9	
Date Sampled	May 2023	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench 08/06/2023

Approved Signatory

Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au