

Client: DIXON SAND (PENRITH) PTY LTD  
PO BOX 148  
PENRITH NSW 2751

Job No 7555/1  
Date: 27/10/2023  
Tested By: LC  
Checked By: AK

Project: MATERIAL ANALYSIS  
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

## TEST RESULTS

<b>TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12</b>			
Material Description	Bricklaying SAND (Yellow)		
Sieve Analysis			
Laboratory Number	7555/1-541		
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying	
9.5mm	100	<b>AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing</b>  <div style="border: 1px solid black; padding: 5px; width: 100px; margin: 0 auto;"> <b>10.9</b> </div>	
4.75mm	100		
2.36mm	99		
1.18mm	83		
600 microns	46		
300 microns	12		
150 microns	2		
75 microns	0.6		
Date Sampled	September 2023		
Sampling Procedure	Sampled by Client - Tested as received		
Sampling Location	Ex Maroota Quarry		

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734  
Corporate Site Number 2727

Head Office:  
34 Borec Road, Penrith NSW 2750  
P O Box 880 Penrith NSW 2751  
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 27/10/2023

Approved Signatory



Prestons Laboratory:  
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170  
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200