

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date Tested: 30/04/2024
Tested By: JF
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING)		
Material Description	Coarse SAND	
Sieve Analysis		
Laboratory Number	7555/1-564	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	
4.75mm	100	
2.36mm	91	
1.18mm	81	
600 microns	64	
300 microns	28	
150 microns	4	
75 microns	1.3	
Date Sampled	16/04/2024	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Accredited for compliance with ISO/IEC 17025.

A Kench 30/04/2024
Approved Signatory

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au