

Client: DIXON SAND (PENRITH) PTY LTD
PO BOX 148
PENRITH NSW 2751

Job No 7555/1
Date: 15/05/2023
Tested By: TS
Checked By: AK

Project: MATERIAL ANALYSIS
MATERIAL TESTING - 4610 OLD NORTHERN ROAD, MAROOTA

TEST RESULTS

Page 1 of 1

TEST PROCEDURE AS1141.11.1 (DRY SIEVING), 12		
Material Description	Bricklaying SAND (Yellow)	
Sieve Analysis		
Laboratory Number	7555/1-527	
<u>Sieve Size</u>	Percentage Passing	Pre-treatment Nil - Standard Oven Drying
9.5mm	100	AS1141.12 Materials finer than 75 microns in Aggregates (by washing) % Passing
4.75mm	100	
2.36mm	97	11.3
1.18mm	89	
600 microns	63	
300 microns	19	
150 microns	3	
75 microns	0.4	
Date Sampled	April 2023	
Sampling Procedure	Sampled by Client - Tested as received	
Sampling Location	Ex Maroota Quarry	

Form No: R 025 Version 05 06/13 - issued by ER



Nata Accreditation Number 2734
Corporate Site Number 2727

Accredited for compliance with ISO/IEC 17025.

A Kench

16/05/2023

Approved Signatory



Head Office:
34 Borec Road, Penrith NSW 2750
P O Box 880 Penrith NSW 2751
Telephone: (02) 4722 2744 Facsimile: (02) 4722 2777

Prestons Laboratory:
Unit 4, 18-20 Whyalla Place, Prestons NSW 2170
Telephone: (02) 9607 6111 Facsimile: (02) 9607 6200

email: info@geotech.com.au www.geotech.com.au