

# MATERIAL SAFETY DATA SHEET

## MIG Wire And TIG Wire

### 1. PRODUCT AND COMPANY DESIGNATION

**Product Name:** CARBON STEEL WELDING WIRES AND RODS  
**Product Specification:** AWS SFA 5.18 (EN 440)  
**Product Classification and Brands:** The following wires and rods are covered by this MSDS:  
 ER 70S-6 Tig 70S-2  
**Recommended use:** Gas Shielded Arc Welding of plain carbon steels  
**Supplier:** Phoenix Welding Wires  
**Address:** C4, C5, C6, Radhe Industrial Estate, Kapadwanj  
**Telephone number:** 8780950131  
**Email ID:** info@phoenixweldingwires.com

### 2. DETAILS OF COMPOSITION

These products consist of a solid carbon steel wire, (with or without a copper protective coating), either continuously wound on reels, spools or in bulk packs, or supplied in straight cut lengths. Specific details of the composition of the wires and rod types covered by this data sheet are given below.

TABLE 1: COMPOSITION DATA (WT %)

AWS Classification	Iron	Carbon	Manganese	Silicon	Copper <sup>1</sup>	Ti	Zr	Al
ER 70S-2	>97	0.07	0.90 to 1.40	0.40 to 0.70	<0.5	0.05 to 0.15	0.02 to 0.12	0.05 to 0.15
ER 70S-6	>96	0.07 to 0.15	1.40 to 1.85	0.80 to 1.15	<0.5	-	-	-

<sup>1</sup> Includes copper coating.

### 3. HAZARDS IDENTIFICATION

There are no recognized hazards associated directly with unused welding consumables prior to welding. Packaged consumables may be heavy, and should be handled and stored with care. FOLLOW MANUAL HANDLING REGULATIONS.

Wire wound on reels or spools, or supplied in bulk packages can be coiled under tension. Take care to avoid the wire uncoiling rapidly when released. WEAR GLOVES AND EYE PROTECTION.

When using these wires and rods as part of the welding process additional potential hazards are likely. These are:

- Electric shock from the welding equipment or electrode. This can be fatal.
- Hot metal spatter and heat, which can cause burns to the hand and body, and may cause fire if in contact with combustible materials.
- UV, IR and light radiation from the arc, which can produce 'arc eye' and possible eye damage to unprotected eyes. WEAR SUITABLE PROTECTIVE EQUIPMENT.
- Fumes produced from the welding consumable, material being welded, and the arc radiation. These consist of:
  - Particulate fume such as complex metal oxides, fluorides, and silicates from the weld materials
  - Gaseous fume such as ozone and nitrogen oxides from the action of arc radiation on the atmosphere, and carbon monoxide and dioxide from the oxidation of carbon in the components and from the shielding gas.

SHORT TERM INHALATION OF THESE FUMES AND GASES MAY LEAD TO IRRITATION OF THE NOSE, THROAT AND EYES.

LONG TERM OVEREXPOSURE OR INHALATION OF HIGH LEVELS OF FUMES MAY RESULT IN HARMFUL EFFECTS TO THE RESPIRATORY SYSTEM, CENTRAL NERVOUS SYSTEM AND LUNGS.

LOCAL EXTRACTION AND /OR VENTILATION SHOULD BE USED TO ENSURE THAT ALL HAZARDOUS INGREDIENTS IN THE FUME ARE KEPT BELOW THEIR INDIVIDUAL OCCUPATIONAL EXPOSURE STANDARDS IN THE WELDER'S AND OTHER WORKERS' BREATHING ZONES.

NOTE: If welding is performed on plated or coated materials such as galvanized steel, excessive fume may be produced which contains additional hazardous components, and may result in metal fume fever and other health effects.

### 4. FIRST AID MEASURES

No first aid measures should be required for the unused wire or rod consumables. During welding:

#### Inhalation

If breathing is difficult, bring the patient in fresh air; breathe in fresh air deeply.

<sup>1</sup> Copper content includes coating

#### For skin burns

Submerge affected area in cold water until burning sensation ceases and refer for immediate medical attention.

#### For eye effects such as arc eye and dusts

Irrigate eye with sterile water, cover with damp dressing and refer for immediate medical attention if irritation persists.

#### Ingestion

Ingestion is considered unlikely due to product form. However, if swallowed do not induce vomiting. Seek medical attention. Advice to doctor: treat symptomatically.

#### Electric shock

If necessary, resuscitate and seek immediate medical attention.

### 5. FIRE PREVENTION MEASURES

No specific measures required for the welding consumable prior to welding.

During welding:

Welding should not be carried out in the presence of flammable materials, vapors, tanks, cisterns and pipes and other containers which have held flammable substances unless these have been checked and certified safe.

### 6. MEASURES IN CASE OF UNINTENTIONAL RELEASE

No specific actions for welding consumable prior to use.

Welding in proximity to stored or used halogenated solvents may produce toxic and irritant gases. Prohibit welding in areas where these solvents are used.

### 7. HANDLING AND STORAGE (FOR SAFETY)

No special precautions are required for these welding consumables.

Welding wires and rods are dense materials and can give rise to a handling hazard when reels, spools, bulk packs or multiple packages are lifted or handled incorrectly or with poor lifting posture.

Good practice for handling and storage should be adopted to prevent physical injuries.

### 8. EXPOSURE PREVENTION/CONTROLS/PERSONAL PROTECTION

#### Exposure Prevention

Welders should not touch live electrical parts, and should insulate themselves from the work and the ground. Manufacturer's guidelines for the use of electrical welding machines should be observed at all times.

Welders and co-workers should be educated about the health hazards associated with welding fume, and trained to keep their heads out of the fume plume.

During welding, fumes and gases will be produced and emitted from the welding process. The content of the fume is dependent on the welding consumables, shielding gas and base materials being welded. The amount and concentration of fume generated is dependent on factors such as current, voltage, welding practices and number of welders in a given area. By following recommended welding practices, fume production can sometimes be minimized.

For the carbon steel solid wires and rods covered in this Data Sheet, the main constituents of the fume will be iron and manganese, mainly in the form of complex oxides and silicates. There will also be smaller amounts of other complex metal oxides and silicates.

Gaseous ozone, nitrogen oxides, carbon monoxide and carbon dioxide are also formed by the effect of the arc on the atmosphere and the shielding gas. In some cases, ozone levels can be high and additional controls may be needed.

The shielding gas used will also affect the fume formation rate, and higher levels of particulate fume will be generated as the percentage of carbon dioxide and oxygen is increased in the shielding gas.

Typical fume composition data for copper-coated and bare carbon steel wires is given below.

TABLE 2: FUME COMPOSITION DATA

GMAW	Solid Wire	Shielding Gas	Iron %	Manganese %	Silicon %	Copper % <sup>2</sup>	Ozone (ppm) <sup>3</sup>
	Bare	CO <sub>2</sub>	45 to 63	5 to 12	1 to 6.0	0.1 to 0.3	0.1 to 1.4 <sup>4</sup>
	Copper Coated	Argon/CO <sub>2</sub>	45 to 55	6 to 12		1.1 to 1.8	0.1 to 0.5 <sup>4</sup>
		Argon/O <sub>2</sub>					

<sup>2</sup> % by weight

<sup>3</sup> ppm = part per million

<sup>4</sup> at 250A and 300mm from arc non-breathing zone

<sup>5</sup> at 250A and 600mm from non-breathing zone

<sup>2</sup> % by weight

<sup>3</sup> ppm = parts per million

<sup>4</sup> at 250 amps and 300mm from arc non-breathing zone

<sup>5</sup> at 250 amps and 600mm from arc non-breathing zone

Additional fume composition data for a solid carbon steel wire welded with different shielding gases are also given below, and the individual exposure limits for the constituents (when specified) are also given. Fume exposure should be controlled to below the recognized exposure limit for each of the individual constituents, and to below 5 mg/m<sup>3</sup> for the total particulate fume.

**TABLE 3: FUME COMPOSITION DATA (WT %)**  
**PARTICULATE FUME COMPOSITION FOR A RANGE OF SHIELDING GASES AND AWS A5.18 ER70S-6 TYPE WIRE (COPPER COATED)**

Shielding Gas	Current Amps	Fe %	Mn %	Cr %	Ni %	Cu %
Carbon Dioxide	180	48.5	9.7	0.08	0.06	1.48
	300	52.1	7.6	0.05	0.06	1.45
Light	180	62.1	7.2	0.11	0.10	1.80
	300	51.8	6.1	0.06	0.05	1.25
Universal	180	45.5	9.2	0.06	0.08	0.29 <sup>6</sup>
	270	51.6	5.8	0.06	0.06	0.12
Heavy	180	51.9	6.9	0.14	0.09	1.74
	300	52.0	6.4	0.05	0.05	1.51

<sup>6</sup> Bare wire, same type

**TABLE 4: HAZARDOUS FUME COMPONENTS**

Welding fume component	CAS No.	OEL 8hr TWA	STEL 15min TWA
Total Welding Fume (particulate)		5	
Iron oxide fume (as Fe)	1309-37-1	5	10
Manganese and its inorganic compounds (as Mn)	7439-96-5	1.0	3
Chromium VI compounds (as Cr)		0.05	
Chromium III compounds (as Cr)		0.05	
Nickel and its inorganic compounds		1	
Water soluble		0.1	
Water insoluble		0.2	
Copper Fume	7440-50-8	0.2	
Nitrogen dioxide	10102-44-0	5.6	9.4
Nitrogen monoxide	10102-43-9		
Ozone	10028-15-6	0.2	
Carbon dioxide	124-38-9	9000	54000
Carbon monoxide	630-08-0	57	458
Aluminum	1344-28-1	5	
Inhalable Respirable dust			

Units are in mg/m<sup>3</sup>, except when stated otherwise.

The fume analyses for the carbon steel wires and rods covered by this data sheet, when used for welding clean, uncoated plain carbon steels, indicate that as long as the 5 mg/m<sup>3</sup> total fume exposure limits are met, fume levels of the other constituents will generally be below their respective exposure limits. The exceptions are manganese, ozone and nitrogen dioxide, as these have low exposure limits and additional controls may be required. THE FUME LEVELS GIVEN ABOVE WERE GENERATED UNDER LABORATORY CONDITIONS WHEN WELDING CLEAN, PLAIN CARBON STEEL UNDER THE MANUFACTURERS RECOMMENDED WELDING PARAMETERS, AND ARE INDICATIVE OF REASONABLY EXPECTED FUME LEVELS. ACTUAL FUME LEVELS WILL VARY IN PRACTICE, DEPENDING ON THE WELDING PARAMETERS AND OTHER CONDITIONS, AND MAY BE HIGHER OR LOWER THAN THOSE LISTED ABOVE.

Additional fume may arise when these WIRES AND RODS are used to weld contaminated base materials, coated or plated steels, other metals and alloys, OR WHEN INCORRECT WELDING CONDITIONS ARE USED. THE ONLY ACCURATE WAY TO DETERMINE THE COMPOSITION AND QUANTITY OF FUMES AND GASES TO WHICH WORKERS ARE EXPOSED IS TO TAKE AIR SAMPLES FROM INSIDE THE WELDERS HELMET, IF WORN, OR IN THE WORKER'S BREATHING ZONES. Individual fume measurements should be made in these cases using recognized sampling and analysis standards. Based on the results of these measurements, additional fume controls may be required to ensure that all the fume constituents are controlled below their exposure limits.

#### Controls

Good general ventilation, and/or local fume extraction at the arc should be used to control the fumes and gases produced during welding to below their individual recognized exposure limits when measured in the welder's and co-workers' breathing zone. In addition, the ventilation and extraction should also be sufficient to ensure that the total particulate fume levels are reduced below 5mg/m<sup>3</sup> when measured in the breathing zone.

In confined spaces where ventilation is not adequate, an air fed breathing system should be used. All precautions for working in confined space should be observed. Refer to OHSAct No.85 of 1993 General Safety Regulation 9. For further information see the American National Standard Z49.1 Safety in Welding and Cutting and SABS 0238 (SANS 10238) Welding and Thermal Cutting Processes – Health and Safety.

Where fume levels exceed the recognized exposure limits, respiratory protection may be required in the form of a Class P2 (metal fume) respirator.

#### Personal Protection

Welders and co-workers in the vicinity should wear protective clothing and eye protection appropriate to arc welding as specified by local standards.

#### Protection of Body and Skin

Suitable clothes for welding should be worn such as non-light reflective fireproof overalls, leather apron, welding helmet, leather boots spats and gloves.

#### Protection of Hands

Welders should wear suitable hand protection such a welding gloves or gauntlets of a suitable standard. Co-worker should also wear suitable hand protection against hot metal, sparks and spatter.

#### Eye Protection

Welders should wear a welding helmet fitted with the appropriate optical welding filter for the operation. Suitable protective welding screens and goggles should be provided, and used by others working in the same area.

### 9. PHYSICAL AND CHEMICAL PROPERTIES

Physical state	Solid
Color	Generally black/grey, or copper colored when coated.
Form	Metal wire or rod
Odor	Odorless
pH	Not available
Vapor pressure	Not relevant
Vapor Density	Not relevant
Boiling point/ range	Not relevant
Melting Point	~1500°C
Solubility in water	Insoluble
Density	Not available
Explosive/ignition point	Nonflammable. No fire or explosion hazard exists

### 10. STABILITY AND REACTIVITY

There are no stability or reactivity hazards from welding wires and rods as supplied.

Hazardous decomposition products such as metal oxide fumes and gases (see Section 8) are produced during welding.

### 11. TOXICITY DATA

Welding fumes if inhaled can potentially produce several differing health effects caused by the metal containing particles and the gases produced during the welding process, both of which are present in the 'fumes'. The exact nature of any likely health effect is dependent on the consumable, material being welded, weld process, all of which affect fume quantity and composition, as well as the use of adequate ventilation, respirators, or breathing equipment as circumstances require.

Inhalation of the fumes/gases produced during welding may lead to irritation to the nose throat and eyes. The range of health effects include respiratory effects with symptoms such as asthma, impaired respiratory and lung function, chronic bronchitis, metal fume fever, pneumoconiosis, possible emphysema and acute pulmonary oedema.

Other potential health effects at elevated levels of exposure include central nervous effects possible lung cancer, bone disease, skin and fertility effects. Which of these health effects is potentially likely is related to the fume composition, and this needs to be consulted with the specific toxicity data below to assess the health risk when using any particular welding process. Unprotected skin exposed to UV and IR radiation from the welding arc may burn or redden, and UV radiation is potentially a carcinogen. UV radiation can affect the unprotected eye by producing an acute condition known as 'arc eye'. Specific effects relevant to major particulate and gaseous fume constituents produced when welding with these wires and rods.

#### Iron

The chief component of fume generated by welding carbon steels is iron oxide. Iron oxide is generally considered a nuisance material and unlikely to cause any significant health effects. The fume particles however accumulate in the lungs and lead to a benign pneumoconiosis called siderosis.

#### Manganese

Manganese compounds are also found in carbon steel welding fumes. Manganese is mainly a systemic chronic toxin, although exposure to high particulate concentrations can cause some respiratory irritation. Overexposure or inhalation of excessive amounts of manganese has been shown to affect pulmonary function, blood and may cause irreversible central nervous system damage (manganism) which resembles Parkinsons disease. Symptoms of manganism include tremors, impaired speech, facial expression changes, slow clumsy movements and eventually impaired walking. The symptoms are typically not apparent for several years.

#### Copper

Copper is one of the main causes of any metal fume fever observed during welding. Metal fume fever is a delayed respiratory effect produced by inhalation of fume. Symptoms include sweating, chills, fever, muscle aches and high temperature. These acute symptoms normally alleviate within 24-48 hours.

#### Ozone and Nitrogen oxides

These gases are formed due to interactions of the arc with the surrounding air. Both gases can produce eye, respiratory and lung irritation and also can produce longer term lung effects such as decreased lung capacity, chronic bronchitis, and emphysema. Of particular concern with both gases is that exposure to high levels (eg due to build up in confined spaces) can result in acute lung effects such as delayed pulmonary oedema.

#### Carbon monoxide and carbon dioxide

Carbon monoxide (CO) is a chemical asphyxiant and its toxicity is due to its affinity for oxygen carrying blood hemoglobin causing fatigue, weakness, dizziness and eventual unconsciousness and possible death. Carbon dioxide (CO<sub>2</sub>) is mainly an asphyxiant but can exert some toxic properties by increasing pulse and heart rate. These gases are mainly formed through decomposition of some electrodes' components, or from oxidation of any carbon in the wires and rods, or from the shielding gas.

<sup>6</sup> Bare wire, same type

---

## 12. ECOLOGICAL DATA

The welding process produces particulate fumes and gases which may cause long term adverse effects in the environment if released directly into the atmosphere. Welding fumes from the arc processes which use the wires and rods covered by this data sheet can produce carbon dioxide gas, which is dangerous to the ozone layer.

---

## 13. DISPOSAL DATA

Packaging and wire and rod scrap should be disposed of as general waste or recycled. No special precautions are required for this product.

---

## 14. TRANSPORT INFORMATION

No special requirements are necessary in transporting these products.

---

## 15. REGULATIONS

- OHSAct No 85 of 1993 General Safety Regulation 9.
  - SABS 0238 (SANS 10238) Welding and Thermal Cutting Processes – Health and Safety.
- 

## 16. OTHER INFORMATION

The customer should provide this Materials Safety Data Sheet to any person involved in the materials use or further distribution. Afrox requests the users (or distributors) of this product to read this Materials Safety Data Sheet carefully before usage. Further information can be obtained from the American National Standard Z49.1 Safety in Welding and Cutting.

The information contained in this Material Safety Data Sheet relates only to the specific materials designated and may not be valid for such material used in combination with any other material or in any process.

Information is given in good faith and is based on the latest information available to Afrox and is, to the best of Afrox's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy, reliability or completeness of the information, and Afrox assumes no responsibility and disclaims any liability incurred in using this information.

The product is supplied on the condition that the user accepts the responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent rights must not be assumed.