

PRODUCT OVERVIEW

	Product Name	Coating Thickness	Coverage (sq ft per gallon)	Dielectric Strength	ASTM B117-18 Salt Spray Test Results
	Corrosion Shield	1-4 mils	200 sq ft/gal	36.8kV	500+ hrs without corrosion
	HD Corrosion Shield	13-20 mils	100 sq ft/gal	3.29kV	1000+ hrs without corrosion
	Anchor Chain Corrosion Control	8-13 mils	150 sq ft/gal	8.92kV	300+ hrs without corrosion
	Bridge & Steel Corrosion Control	8-13 mils	150 sq ft/gal	8.92kV	300+ hrs without corrosion
	Automotive Rust Proofing	8-13 mils	150 sq ft/gal	8.92kV	300+ hrs without corrosion
	Wire Rope Corrosion Control	1-4 mils	200 sq ft/gal	N/A	100+ hrs without corrosion
	Void & Rudder Float Coat	1-4 mils	200 sq ft/gal	36.8kV	500+ hrs without corrosion
	Di-Electric spray	1-4 mils	200 sq ft/gal	40.6kV	100+ hrs without corrosion
	5 in 1 Wipes	1-4 mils	N/A	40.6kV	N/A
	PLID Wrap Anti-Corrosion Tape	30.1 mils	Requires 30% overlap	140V/mil	1000+ hrs without corrosion