#### 07-Photovoltaics Part 1

ECEGR 4530 Renewable Energy Systems



#### Overview

- PV Industry
- PV Basics
- Silicon
- PV Physics
- Diffusion and Drift
- N- and P-Type Material
- PN Junction
- Bias



#### Introduction


- Photoelectric Effect is the mechanism by which solar photovoltaic (PV) works
- Electricity is directly generated
- Discovered by Edmond Becquerel in 1839
- Established for power generation in 1954 by Chapin, Fuller and Pearson





## **PV Industry**

- Reported installed PV capacity: 227 GW
  - ~50 GW added in 2015





## Leading Countries (2015)

1. China: 43 GW

2. Germany: 40 GW

3. Japan: 34 GW


4. US: 26 GW

5. Italy: 19 GW




### **PV Industry**

- Total US PV capacity: 13,000 MW (2014)
  - 4,751 MW added in 2013 (41% growth)






### PV Industry



Source: SEIA.org




#### Solar Costs



Note: these Are total costs, not just for the panels




#### Solar Costs



PV panels cost ~\$0.50/Watt



## Solar in the U.S.





#### **PV** Basics

- Advantages of PV
  - Zero fuel costs
  - Availability of fuel (still produces energy if there is no DNI)
  - No moving parts (no noise, reduces maintenance)
  - Modular design (can also be integrated into buildings)
  - No emissions




#### **PV** Basics

- Disadvantages of PV
  - high capital costs (decreasing)
  - low efficiency
  - use of toxic materials in some manufacturing processes
  - need for power electronic inverter (DC/AC converter) for grid-connected applications
  - intermittent and variable
  - cloud cover is difficult to predict



#### Solar PV Costs



Source: SEIA.org



# **PV Industry**







monocrystalline

polycrystalline

thin film



#### **PV** Basics

- PV cells produce electricity when photons illuminate a pn junction
- Photon excites an electron out of the valence band into the conduction band
- Built-in electrostatic field pushes the electron through the circuit
- pn junctions are common in semiconductors




#### Silicon

- Silicon (Si) is often used in semiconductors
- 2<sup>nd</sup> most abundant element on Earth
- Si is Group 14 Element (old IUPAC Group IV)
  - 4 outer (valence) electrons
  - Silicon crystal forms a diamond lattice
  - Each Si atom shares 2 electrons with its neighbors



# Silicon






#### Silicon

- Valence electrons largely dictate the electrical properties of a material
- Silicon crystal: all valence electrons are tightly held in covalent bonds
- Energy of the electron must fall within welldefined bands (quantum theory)



- Add enough energy to an electron in the valence band and it "jumps" to the conduction band
- Free electron: electron in the conduction band
- Free electrons can flow through the circuit or drop back into the valence band (recombination)






- The required energy is known as the Energy Gap
- Energy Gap is fundamental to the operation of PV
- Energy Gap varies with type of semiconductor
  - Crystalline Si: 1.1 eV (electron-volt, 1.6 x 10<sup>-19</sup>)
  - Amorphous Si: ~1.75 eV



- Hole: silicon with a missing electron (net positive charge)
- Hole may attract an electron from a neighbor
- Process may repeat and hence, the hole propagates

Dr. Louie 2:







#### Diffusion and Drift

- Holes and free electrons move through the Si crystal by two mechanisms: diffusion and drift
- Note: current flows in a direction <u>opposite</u> of the direction of the electrons
- If free electrons are evenly distributed and there is no external electric field, then the free electrons move randomly
  - No net current



#### Diffusion and Drift

- If concentrations of electrons exist, then:
  - Diffusion (I<sub>D</sub>): process of electrons distributing themselves from regions of high concentration to low concentration, independent of an applied electric field
- External electric field causes movement:
  - Drift (I<sub>S</sub>): electrons move toward positive electric field (current away from positive)



### Doped Silicon

- In pure Si (intrinsic) there are very few free electrons (recombination quickly occurs)
  - Intrinsic Si is an insulator
- To promote free electrons, Si is doped
  - n-type material
  - p-type material




- Introduce Phosphorus into the Si lattice
  - P
  - Atomic weight 15
  - 5 valence electrons
- 4 valence electrons form bonds with neighboring Si, the 5<sup>th</sup> must be in the conduction band



- Does P-doped silicon have a net charge?
  - Yes
  - No



- Does P-doped silicon have a net charge?
  - Yes




• electrons = protons



- Note: no hole is generated, even if free electron moves away
- No net charge

P becomes a positive ion if electron moves away





### N-type Material Recap

- Doping intrinsic Si with P
  - Increases the number of free electrons
  - Material becomes a conductor
  - Does not lead to an overall net charge
  - Does not create holes (though holes may exist due to thermal excitation of electrons, known as minority carriers in n-type material)
- Other elements (known as donors) other than P (Group V) can be added



### P-Type Material


- Introduce Boron into the Si lattice
  - B
  - Atomic weight 13
  - 3 valence electrons
- 3 valence electrons form covalent bond
- 1 hole remains
- Free electrons may exist due to thermal excitation (free electrons are minority carriers in p-type material)



## P-Type Material

- No free electrons are generated
- No net charge

If a free electron fills the hole, then B is a





- P-type material has more free electrons than Ntype material
  - True
  - False
- P-type material has a positive charge
  - True
  - False




- P-type material has more free electrons than Ntype material
  - True
  - False
- P-type material has a positive charge
  - True
  - False



#### PN Junction


- What happens when p-type material and n-type material are placed next to each other?
  - Note: they are formed together from a continuous crystal, not a mechanical junction






#### PN Junction

- Again, there is no net charge
- What happens next?
  - Diffusion!






Diffusion current from p-type to n-type



junction p-type n-type




- As free electrons move from n-type to p-type they quickly find holes and <u>recombine</u> near the junction
  - Analogous process happens with holes leaving the p-type



junction p-type n-type




- Now the p-type material has more electrons than protons, so it develops a net negative charge (and electric field)
- Electric field opposes more electrons from moving from the n-type to the p-type depletion region






# In the Depletion Region






# In the <u>Depletion</u> Region






- V<sub>0</sub>: voltage across depletion region, usually 0.8 V at room temperature
- Note there still is no voltage across the entire material






- Minority carriers on either side near or in the depletion region can be swept across the depletion region by the electric field
  - this is Drift current






- In open circuit conditions, drift current must equal diffusion current  $I_D = I_S$ 
  - For example, a minority electron diffusing to the ntype side will increase the concentration of electrons there which will cause increased diffusion across the depletion region






#### Bias


- Now assume a battery is connected to the contacts of the pn junction
- There are two ways of doing this
  - Forward bias
  - Reverse bias








- Positive charge from the battery pushes the holes in the p-type toward the depletion zone
- Negative charge from the battery pushes the free electrons in the n-type toward the depletion zone








- Net result is that the electric field preventing diffusion decreases
- Diffusion current increases (I<sub>D</sub>)

$$I_D - I_S = I$$





The current is determined from:

$$I = I_{Sat} \left( e^{V/V_T} - 1 \right)$$
 and  $V_T = \frac{kT}{q}$ 

- Where:
  - k: Boltzmann's constant (1.38 x 10<sup>-23</sup> J/K)
  - T: temperature in K
  - q: charge 1.602 x 10<sup>-19</sup> (C)
  - I<sub>sat</sub>: reverse bias saturation current (A)
- V<sub>t</sub> is usually ~25mV





- I<sub>sat</sub> is a function of temperature, junction area and other physical characteristics of the junction
  - Usually around 10<sup>-10</sup> A (though could be several orders of magnitude larger or smaller)



#### Reverse Bias

- Holes in the p-type material are pulled away from the junction
- Electrons are pulled away from the n-type material
- Net result: <u>depletion region increases</u>








#### Reverse Bias

- Electric field increases strength
- Diffusion current decreases
- Drift current remains unaffected
- I remains small





- The described operation is exactly the same as a diode
- Forward Bias: large current
- Reverse Bias: <u>very</u> small current


$$I \longrightarrow I \longrightarrow I$$
Forward Bias


Reverse Bias

Current through a diode:

$$I = I_{Sat} \left( e^{V/V_{T}} - 1 \right)$$










- No net current flows in un-illuminated PN junction
  - Exception: external battery connected
- What happens when a photon hits the PN Junction?
- Recall:
  - Photons can excite electrons into the conduction band






- If a photon hits an electron in the p-type material that is close to (or within) the depletion region, then the electron will be pushed across by the electric field
  - Drift current results
- This is called illumination current (I<sub>L</sub>)

$$I = I_{L} - I_{Sat} \left( e^{V/V_{T}} - 1 \right)$$





Using active circuit convention





 We are interested in the short circuit current and open circuit voltage of a PV cell







Under short circuit conditions

$$I_{SC} = I_L - I_{Sat} \left( e^{0/V_T} - 1 \right)$$

$$\Rightarrow I_{SC} = I_L$$

$$p-type \qquad n-type$$



Computing the open circuit voltage

$$\begin{split} I &= I_L - I_{Sat} \left( e^{V_{OC}/V_T} - 1 \right) = 0 \\ &\Rightarrow \frac{I_L}{I_{Sat}} + 1 = \left( e^{V_{OC}/V_T} \right) \cong \frac{I_L}{I_{Sat}} \quad \text{sin} \, ce \, I_L >>> I_{Sat} \\ &\Rightarrow \ln \left( \frac{I_L}{I_{Sat}} \right) = \frac{V_{OC}}{V_T} \\ &\Rightarrow V_T \ln \left( \frac{I_L}{I_{Sat}} \right) = V_{OC} \quad \text{(open circuit)} \end{split}$$



### V-I Characteristics

• 
$$I_{sat} = 10^{-10}$$

• 
$$V_t = 25mV$$

• 
$$I_L = 1.5 A$$

