

TEST METHOD

PHYSICAL PROPERTIES

1. APPARENT DENSITY	ASTM C97-18	2.2 – 2.45 g/cc
2. WATER ABSORPTION	ASTM C97-18	<0.05 %

MECHANICAL PROPERTIES

1. FLEXURAL STRENGTH	ASTM C880	>45 Mpa
2. ABRASION RESISTANCE	ASTM C501	0.19 – 0.21 gm
3. IMPACT RESISTANCE	ASTM D256-10	>5 Nm
4. MOHs HARDNESS	ASTM C241	6.5

SLAB DETAILS

DIMENSION	THICKNESS	SLAB WEIGHT (15/20/30 mm)
JUMBO - 128 x 64 in	15mm/20mm/30mm	36 / 47 / 70 - kg / m ²



NSF CERTIFIED
NSF/ANSI 51 Food Equipment Material, Safe for Food & Water contact.



ISO 9001 / 14001 / 45001 CERTIFIED
State-of-the -Art manufacturing facility



GREENGUARD GOLD CERTIFIED
Safe for Indoor Use.
No Toxic / Volatile Emissions.



KOSHER CERTIFIED
Compliant with religious dietary laws of the Jewish faith.

**All values given above are indicative and are mean value of repeated tests.*

<https://inspiredquartz.com/>