

	Test Method	Units	Min / Typical
Thickness		mil.	45
Breaking Strength (warp/fill)	ASTM D751A	lbs	300/250 - 350/325
Break Elongation (warp/fill)	ASTM D751A	%	22/22 - 35/35
Tear Strength (warp/fill)	ASTM D5884	lbs	100/100 - 140/140
Hydrostatic Resistance	ASTM D751A	psi	350 - 450
Puncture Resistance (pyramid)	Method 2031	lbs	300 - 350
Puncture Resistance (flat Tip)	ASTM D4833	lbs	85 - 90
Ply Adhesion	ASTM D751	lbs / in	40/2 - 50/2
Dimensional Stability	ASTM D1204	% max	1.0 - 0.5
Abrasion Resistance (H18/1 kg)	ASTM D3389	cycles	7,500 - 10,000
Low Temperature Bend	ASTM D2136	F°	-40 - -40
UV Resistance - No Chalking/Cracking	ASTM D7238	hrs	20,000 - 40,000
UV Resistance (20K hrs.) Tensile Strength and Elongation Retained	ASTM D751	%	>50 - >92
Bonded Seam Strength	ASTM D7749	lbs	200 - 260
Seam Peel Adhesion	ASTM D6636	lbs / in	20 - 35

RPP is a flexible geomembrane resulting in no stress cracking. This geomembrane is also UV resistant, has high tear strength and puncture resistance.

RPP, or Reinforced Polypropylene, is a scrim reinforced product heat welded by a trained technician. Color options are available upon request. At WPL Fab we test each panel, accordion fold then roll onto a core, package with a protective layer and apply directions on the outside of the roll for ease of deployment.

### Applications

Ponds, Lakes, Canals, Drop-In Tank Liners, Potable Water Storage, Irrigation Reservoirs

The ATLAS logo is displayed in a large, bold, sans-serif font. It is centered over a stylized, dark blue and black image of a globe, showing the continents of North and South America.

15847 Kimberlee St.  
Houston, TX 77049  
WPL-Fab.com