

Test Method		Units	Thickness
Thickness	ASTM D1777	mil	12 ± 10
Grab Tensile	ASTM D7004	lb	MD 180 TD 125
Strip Tensile	ASTM D7003	lb / in	MD 140 TD 100
Tongue Tear	ASTM D5884	lb / in	MD 50 TD 50
Mullen Burst	ASTM D751	psi	275
MVRT	ASTM E96		0.35 g/m ² x 24 hrs
Hydraulic Conductivity	Calc. from MVRT	cm / s	1.37 x 10 ⁻¹⁴
Hydrostatic Resistance	ASTM D751	psi	130
Puncture Resistance	ASTM D4833	lb	76
CBR Static Puncture	ASTM D6241	lb	530
Dimensional Stability	ASTM D1204	%	MD -2.9 TD -2.2
Low Temp. Flex	ASTM D2136	°F	MD & TD Pass @ -40
HP - OIT	ASTM D5885	min	1330
Accelerated UV Weathering	ASTM D7238	hrs	<90 @ 2k hrs

WC geomembranes are developed as a medium to heavy weight liner incorporating a new coating recipe designed to improve toughness and abrasion resistance. With the ability to withstand puncture and UV rays this product is a solution to many projects.

Woven Coated is heat welded by a trained technician or has the option to be taped on site. At WPL Fab we test each panel, accordion fold then roll onto a core, package with a protective layer and apply directions on the outside of the roll for ease of deployment.

Applications

Short Term liners, Secondary Containment, Containment Ponds, Sport Fields



ATLAS

15847 Kimberlee St.
Houston, TX 77049
WPL-Fab.com

