

Auris Noble LLC
Sidney Resources Corporation Samples 10-14-2024

P241009-08	P241009-09	P241009-10	P241009-11	P241009-12	P241009-13	P241009-14	
	SID-001-A	SID-001-B	SID-001-C	SID-001-D	SID-001-E	SID-001-F	SID-001-G
	Table Feed	Super-Con non-pulverized	Super-Con pulverized	Super-Con non-pulverized	Super-Con pulverized	Super-Con non-pulverized	Super-Con pulverized
Net (g)	999.0	50.665	50.960	100.685	100.484	100.858	101.309
Ag(%wt)	0.0110	0.101	0.120	0.0996	0.141	0.120	0.131
Al(%wt)	7.53	2.07	1.95	2.20	1.80	2.05	1.88
As(%wt)	0.05	1.58	1.63	1.59	1.61	1.65	1.45
Au(%wt)	0.0454	0.0409	0.0423	0.0449	0.0389	0.0336	0.0438
Ca(%wt)	1.43	2.72	2.79	2.76	2.78	2.66	2.70
Fe(%wt)	1.45	41.08	41.59	23.28	42.33	41.11	41.56
Ir(%wt)	< 0.0015	< 0.0016	< 0.0015	< 0.0015	< 0.0015	< 0.0015	< 0.0015
K(%wt)	4.85	2.22	2.35	2.30	2.29	2.09	2.08
Pd(%wt)	< 0.0015	< 0.0016	< 0.0015	< 0.0015	< 0.0015	< 0.0015	< 0.0015
Pt(%wt)	< 0.0046	< 0.0047	< 0.0044	< 0.0046	< 0.0046	< 0.0046	< 0.0045
Rh(%wt)	< 0.0019	< 0.0020	< 0.0018	< 0.0019	< 0.0019	< 0.0019	< 0.0019
Ru(%wt)	< 0.0029	< 0.0030	< 0.0028	< 0.0029	< 0.0029	< 0.0029	< 0.0028
Si(%wt)	34.43	8.19	7.79	8.28	7.95	7.92	8.02



Patrick Deeringer
Chief Operating Officer
Auris Noble LLC



a: 160 E Voris St, Akron, OH 44311