

Concentrates are settled in a small tank, dried in 300-pound lots on an electrically heated drying pan, and sacked for shipment. The following analysis of a concentrate shipment is fairly typical, although some shipments are much higher-grade; the gold-silver ratio varies greatly from one shipment to another.

33/ Lindgren, Waldemar, work cited (see footnote 32).

34/ Reed, J. C., work cited (see footnote 18).

6896

- 77 -

I. C. 7039

Gold.....	ounces per ton	4.66
Silver.....	do.	85.71
Copper.....	percent	.25
Lead.....	do.	1.6
Zinc.....	do.	.8
Iron.....	do.	22.8
Sulphur.....	do.	24.4
Lime.....	do.	1.0
Insoluble.....	do.	37.6