# Pro-Seal PP/PK III primer A®



Pro-Seal PowerKote Part- A, of Harsh Chemical Environment Barrier System

### **Product Description**

**Pro-Seal PP/PK III primer Part A®** is part A of a polycarbon/ polycarbonate high density two-part chemical and wear resistant top coating. This product must be mixed with Pro-Seal PP/PK III primer B® part-B and is designed to approach an entire infrastructure repair or new construction challenge.

### Advantages:

- Easy to install
- Performs in harsh chemical environments
- Impervious to U.V. attack
- Easily spot repairable

### **Applications:**

- Primary Containment
- Secondary Containment
- Structural Preservation
- Rehabilitation
- Cosmetic improvement to high traffic, and chemically exposed areas

#### **Technical**

Information	Value
Material	2 part
Mix time	4 minutes
Appearance	Paste
Application	See guide specification
Flash point	500°F
Pot life	45 minutes
Stain resistance	Excellent
Application per coat	1-120 mils
Cure to walkable	6-12 hours
Full cure	96 hours
Packaging:	2-part kit

#### Instructions

**1.** Surface must be properly prepared, dry, clean, and free of all loose particulate and all bond-breaking matter and fluids.

2. For specific use application instructions or guide specifications, contact Pro-Seal's Technical Department at Pro-Seals toll free USA/Canada 800.349.7325, Int'l +1 205 451 9527 and/or email Pro-Seal Technical dept. at <a href="mailto:information@prosealproducts.com">information@prosealproducts.com</a>

### **Technical Support**

Contact Pro-Seals technical department at USA/Canada 800.349.7325, Int'l +1 206 452 9527 or <a href="mailto:information@prosealproducts.com">information@prosealproducts.com</a> for complete guide specifications in AIA format for your easy down load and incorporation into your project.

\*Extended long-term warranties are available for Pro-Seal Authorized applicators, for Pro-Seal warranty approved, projects.

### **Specifications**

Test		Data	Value
ASTM 695	D	Compressive strength	24,000 psi
ASTM 1 1706	D	Cured hardness	D 88 shore
ASTM I 790	D	Flexural strength	6,160 psi
ASTM 1 1002	D	Adhesive tensile sheer	2,600 psi
ASTM 638	D	Tensile strength	3,200 psi
ASTM 1 2586	D	Cure shrinkage	.002 in
Taber abrasion resistance		500 gm head cs 17wheel wt. loss 1,000 cycles 350,000 cycles	0.0 mg .0008 mg
FST 141 method 4044	Α	Total solids	100%
FST 141 method 4291	Α	Viscosity mixed 2 parts	8,000 cps

<sup>\*</sup> Data based on laboratory tested materials.



# Pro-Seal PP/PK III primer A®



Pro-Seal PowerKote Part- A, of Harsh Chemical Environment Barrier System

#### **Chemical Resistance**

Cured material	Rating
Hydrochloric acid	Excellent
Sulfuric acid 60%	Excellent
Nitric acid 25%	Excellent
Chromic acid	Excellent
Kerosene	Excellent
Methanol	Excellent
Toluene	Excellent
Ammonia	Excellent
Nitrates	Excellent
Chlorinated solvent	Excellent
Phenol	Excellent
Sodium hydroxide 10%	Excellent
Sulfates	Excellent



The basics, prep, prime coat, then build up coat and topcoat. Pro-Seal PP/PK III primer <sup>®</sup> is for resistance to the harsh vapors above the effluent line, below, in this coolant collection tank.





Wastewater Tank



## Pickling Plant

#### Cautions:

Pro-Seal PowerKote III part-A must be mixed with Pro-seal PowerKote part-B just prior to application. Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

## **Limited Warranty**

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

16541 Redmond Way • Suite 363C • Redmond, WA 98052 Phone: 800.349.7325 • <u>information@prosealproducts.com</u> www.prosealproducts.com • © Copyright Pro-Seal

