Pro-Seal Power Kote AGV™

High Abrasion Traffic Coating

Product Description:

Power Kote AGV™ is a three-component coating for high abrasion traffic surfaces. This product was originally designed for automated guidance vehicle trackways in automotive manufacturing plants. *Polycarbon/polycarbonate integrated technology.

- Easy to install
- No primer required
- 100% solid
- · Easy clean up
- Cost effective

Applications for High Abrasion Traffic:

- AGV trackways
- Coal chutes
- Grain elevators
- Roller paths

Application Instructions:

Surface must be clean and free of all loose particulate and bond-breaking matter. For specific application instructions or guide specifications, contact Pro-Seal's Technical Department at 800.349.7325 or information@prosealproducts.com

Technical

| Information | Value |
|-----------------------|------------|
| Material | 3 part |
| Mix time A + B | 3 minutes |
| Mix time A/B + C | 2 minutes |
| Stain resistance | Excellent |
| Cure to light traffic | 2 hours |
| Full cure | 96 hours |
| Packaging: | 3 part kit |

Technical Support:

Contact our technical department at 800.349.7325, information@prosealproducts.com or visit our website www.proseaproducts.com for additional information



Chemical Resistance

| Cured material | Rating |
|----------------------|-----------|
| Hydrochloric acid | Excellent |
| Sulfuric acid 60% | Very good |
| Nitric acid | Fair |
| Chromic acid | Very good |
| Kerosene | Excellent |
| Methanol | Very good |
| Toluene | Excellent |
| Ammonia | Excellent |
| Nitrates | Fair |
| Sulfates | Very good |
| Phenol | Fair |
| Sodium hydroxide 10% | Excellent |
| Chlorinated solvent | Very good |

Specifications

| Test | Data | Value |
|---------------------------|--|-------------|
| ASTM D 695 | Compressive strength | 33,000 psi |
| | | |
| ASTM D 1706 | Cured hardness | 90 shore D |
| ASTM D 790 | Flexural strength | 6,600 psi |
| ASTM D 1002 | Adhesive tensile sheer | 3,200 psi |
| ASTM D 638 | Tensile strength | 5,800 psi |
| ASTM D 2566 | Cure shrinkage | .003 inches |
| Taber abrasion resistance | 1,000 gm head cs 17 wheel weight loss 1,000 cycles | .00 mg |
| Taber abrasion resistance | 1,000 gm head cs 17 wheel weight loss 350,000 cycles | .006 mg |

^{*} Data based on laboratory tested materials.





Pro-Seal Power Kote AGV™

High Abrasion Traffic Coating

Pro-Seal AGV is for high abrasion warehouse and industrial production floors, DORR thickeners, and other surfaces where production function is impactful to the floor finish.





Cautions:

Keep out of reach of children. May cause skin or eye irritation. This product may be harmful if swallowed. Do not induce vomiting. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

Limited Warranty:

Distributed By:

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations, made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

