Pro-Seal PowerKote III®



Pro-Seal PowerKote Part- A, of Harsh Chemical Environment Barrier System

Product Description

PowerKote III Part A® is part A of a polycarbon/ polycarbonate high density two-part chemical and wear resistant coating. This product must be mixed with Pro-Seal PowerKote III B® part-B and is designed to approach an entire infrastructure repair or new construction challenge.

Advantages:

- Easy to install
- Performs in harsh chemical environments
- Impervious to U.V. attack
- Easily spot repairable

Applications:

- Primary Containment
- Secondary Containment
- Structural Preservation
- Rehabilitation
- Cosmetic improvement to high traffic, and chemically exposed areas

Technical

| Information | Value |
|----------------------|-------------------------|
| Material | 2 part |
| Mix time | 4 minutes |
| Appearance | Paste |
| Application | See guide specification |
| Flash point | 500°F |
| Pot life | 45 minutes |
| Stain resistance | Excellent |
| Application per coat | 1-120 mils |
| Cure to walkable | 6-12 hours |
| Full cure | 96 hours |
| Packaging: | 2-part kit |

Instructions

1. Surface must be properly prepared, dry, clean, and free of all loose particulate and all bond-breaking matter and fluids.

 For specific use application instructions or guide specifications, contact Pro-Seal's Technical Department at Pro-Seals toll free USA/Canada 800.349.7325, Int'l +1 205 451 9527 and/or email Pro-Seal Technical dept. at information@prosealproducts.com

Technical Support

Contact Pro-Seals technical department at USA/Canada 800.349.7325, Int'l +1 206 452 9527 or information@prosealproducts.com for complete guide specifications in AIA format for your easy down load and incorporation into your project.

*Extended long-term warranties are available for Pro-Seal Authorized applicators, for Pro-Seal warranty approved, projects.

Specifications

| Test | | Data | Value |
|---------------------------------|---|--|--------------------|
| ASTM 695 | D | Compressive strength | 24,000 psi |
| ASTM 1706 | D | Cured hardness | D 88 shore |
| ASTM 790 | D | Flexural strength | 6,160 psi |
| ASTM 1002 | D | Adhesive tensile sheer | 2,600 psi |
| ASTM 638 | D | Tensile strength | 3,200 psi |
| ASTM 2586 | D | Cure shrinkage | .002 in |
| Taber abrasion resistance | | 500 gm head cs 17wheel wt. loss 1,000 cycles 350,000 cycles | 0.0 mg .0008 mg |
| FST 141 method 4044 | Α | Total solids | 100% |
| FST 141 method 4291 | Α | Viscosity mixed 2 parts | 8,000 cps |

^{*} Data based on laboratory tested materials.



Pro-Seal PowerKote III®



Pro-Seal PowerKote Part- A, of Harsh Chemical Environment Barrier System

Chemical Resistance

| Cured material | Rating |
|----------------------|-----------|
| Hydrochloric acid | Excellent |
| Sulfuric acid 60% | Excellent |
| Nitric acid 25% | Excellent |
| Chromic acid | Excellent |
| Kerosene | Excellent |
| Methanol | Excellent |
| Toluene | Excellent |
| Ammonia | Excellent |
| Nitrates | Excellent |
| Chlorinated solvent | Excellent |
| Phenol | Excellent |
| Sodium hydroxide 10% | Excellent |
| Sulfates | Excellent |



The basics, prep, prime coat, build up coat and topcoat. Pro-Seal PowerKote III[®] is for resistance to the harsh vapors above the effluent line, below, in this coolant collection tank.





Wastewater Tank



Pickling Plant

Cautions:

Pro-Seal PowerKote III part-A must be mixed with Pro-seal PowerKote part-B just prior to application. Keep out of reach of children. May cause skin or eye irritation. May be harmful if swallowed. Do not induce vomiting. Use in well ventilated areas. Contact a physician immediately and always seek a physician's advice regarding first aid. Use only in commercial or industrial applications. Use only on intended surfaces. Contact manufacturer for specific application uses. See material safety data sheet for additional cautions.

Limited Warranty

We warrant our product to be free of defects in material and workmanship; and to be in accordance with our company quality control standards. All data, statements, and recommendations made herein are based upon information we believe to be reliable, but are made without any representation, guarantee, or warranty of accuracy. Our products are sold on the condition that the user himself will evaluate them, as well as our recommendations, to determine their suitability for the user's own purpose before adoption. Also, statements regarding the use of our products or processes are not to be construed as recommendations for their use in violation of any patent rights or in violation of any applicable laws or regulations. Liability under any condition shall be limited to replacement of material only.

16541 Redmond Way • Suite 363C • Redmond, WA 98052 Phone: 800.349.7325 • <u>information@prosealproducts.com</u> www.prosealproducts.com • © Copyright Pro-Seal

