

SL METALS CORPORATION

Secondary Aluminum Alloy — Recycled ingots/sows

This reference document is for SL Metals customers and commercial counterparts in USA, Japan, China, Europe, and South America. All alloys are available in ingot/sows form, with full Certificate of Analysis (CoA).

	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Pb	Sn	Ti	Al
AlSiCu - standard	4.0-6.0	1.0	1.5-3.5	0.8	0.85	0.15	0.5	1.5	0.2	0.2	0.2	Bal.
AlSiCu custom Zn 1.5, Mg 0.5	2.0-8.0	1.0	1.0 min	0.8	0.5	0.15	0.5	1.5	0.2	0.2	0.2	Bal.
ADC12 – off-grade	8.0-11.0	1.0	1.5 min	0.5	0.5	0.15	0.5	1.0	0.2	0.2	0.2	Bal.
AlSiCu custom Zn 1.0, Mg 0.5	2.0-8.0	1.0	1.0 min	0.8	0.5	0.15	0.5	1.0	0.2	0.2	0.2	Bal.
AlSiCu custom Zn 1.0, Mg 0.3	2.0-8.0	1.0	1.0 min	0.8	0.3	0.15	0.5	1.0	0.2	0.2	0.2	Bal.
AlSiCu custom Zn 1.0, Mg 0.1	2.0-8.0	1.0	1.0 min	0.8	0.1	0.15	0.5	1.0	0.2	0.2	0.2	Bal.
AlSiCu low Cu	2.5 min	1.0	1.0 min	0.8	0.5	0.15	0.5	2.0	0.2	0.2	0.2	Bal.
AV95	0.5	0.5	1.0-2.0	0.3	2.0	0.15	0.2	5.0	0.1	0.1	0.1	Bal.
AL98	0.5	0.5	0.1	0.1	0.2	0.1	0.1	0.2	0.1	0.1	0.1	Bal.
AL99	0.2	0.3	0.05	0.05	0.05	0.01	0.05	0.05	0.05	0.05	0.05	Bal.
AlSiCu High Si / Fe	9.0-10.0	3.5	0.3	0.1	0.1	0.05	0.1	0.1	0.05	0.05	0.05	Bal.
AlSiCu High Si / low Mg	10.0-12.0	0.5	0.2	0.3	0.1	0.01	0.01	0.2	0.01	0.01	0.1	Bal.

Typical analysis



Contact & Quote Requests

To request a quote, please provide: alloy grade (or local standard designation), quantity (MT or FCL), destination port, packaging preference, and company introduction.

SL Metals Corporation | 134 S. Dixie Hwy, Suite 212, Hallandale Beach, FL 33009, USA

Tel: +1.305.320.4433 | Email: info@slmet.com | Web: www.slmet.com

WeChat / WhatsApp available upon request