



GREENTECH™ 286

DESCRIPTION:

GreenTech 286 is a non-ozone depleting, 245fa-blown spray polyurethane foam (SPF). It is designed for insulation and watertight sealing of low sloped roofing applications in residential, industrial and commercial structures. It is also suitable for many other exterior and interior weatherization applications. As a roofing product GreenTech 286 is easy to apply a monolithic surface and smooth outer skin that will maximize coverage rates for topcoat products. When applied with an approved coating GreenTech 286 provides a durable roofing system that meets UL 790 with approved coating.

Physical Property	Test	Result
Core Density (nominal)	ASTM D-1622	2.8 lb/ft ³
R-Value	ASTM C-518	6.9 @ 1"
Tensile Strength (psi)	ASTM D-1623	65-75
Compressive Strength	ASTM D-1621	45-55
Water Vapor Permeability (perm)@ 2"	ASTM E-96	0.8
Air Leakage (L/s/m ² @75Pa @ 1")	ASTM E-283	0.002
Dimensional Stability (%)	ASTM D-2126	<5 Δ
Fire Rating	E-84	NA
Flame Spread Index	E-84	NA
Smoke Development	E-84	NA
Closed Cell Content (%)	ASTM D-2856	98
Viscosity (cps) B Component	ASTM D-2196	700-800
A Component		200-250

Typical Uses

- Insulation Foam for; roofing, storage tanks, exterior walls and any application requiring a watertight seal with thermal insulation properties.
- Residential, Commercial, Industrial.

Features and Benefits

- Meets Class 1.
- Meets UL 790 .
- Low Odor during application. Produces no toxic vapors after installation.
- 245fa-blown; no ozone depleting, VOCs, HFCs and is PBDE-free.
- Monolithic Seal minimizes thermal conductivity and a watertight seal.
- Self-flashing around protrusions of all shapes and contour.
- Lightweight per square foot.

Process Guidelines

- *Condition material to 75°-85° F prior to application. Material that is cold or too hot may result in off ratio mixing.
- Equipment Temperatures for hose and preheaters set; 110°-145° F.
- Equipment Pressure; 900-1500 psi.
- Substrate; 50° – 105° F
- Ambient; 50° - 105° F
- Substrate Moisture; < 19%
- Cream Time @ 77° F; 3-5 seconds
- Rise Time @ 77° F; 8-18 seconds

PREPARATION: GreenTech 286 resin (B) does not require agitation. Do not pre-heat or recirculate resin (B) as doing so will result in the “boiling off” of the 245fa blowing agent which will result in poor yield and poor foam performance.

APPLICATION INSTRUCTIONS: GreenTech 286 is installed by independent SPF contractors. It is recommended that building owners verify that the SPF insulation contractor maintains proper credentials, insurance, and licenses and is properly trained to safely install SPF insulation products.

GreenTech 286 demonstrates excellent adhesion to various substrates when installed according to manufacturer specifications. Allow a minimum of 1 hours for full off-gas and cure before application of a primer, topcoat, or intumescent paint. For best results apply primer, topcoat, or intumescent coating within 72 hours of installation of foam. GreenTech 286 should be installed at a maximum thickness of 4 inches per pass with a minimum of 30 minutes between passes. IT IS THE APPLICATOR'S RESPONSIBILITY TO TEST LIFT THICKNESS FOR A PARTICULAR APPLICATION PRIOR TO COMMENCING INSTALLATION TO ENSURE THAT THE PRODUCT CAN BE INSTALLED SAFELY AT THE DESIRED THICKNESS WITHOUT RISK OF CHARRING OR FIRE.

GreenTech 286 should not be left exposed to sunlight, as UV light will rapidly degrade foam. Do not use near high heat or open flame. Do not apply when Relative Humidity is higher than 80%.

GreenTech 286 must be covered with an approved 15-minute thermal barrier when used as insulation for residential or commercial buildings. Installation must comply with all applicable building codes. Do not install GreenTech 286 at a thickness exceeding 2 inches per pass and do not apply subsequent passes within 30 minutes of the previous pass.

SUBSTRATES: GreenTech 286 is chemically & physically compatible with most common building materials including electrical wiring, wood, metal, concrete, plastic (PVC), copper, vinyl, and glass. It is the responsibility of the contractor to check substrate compatibility prior to starting of the job.

HOW SUPPLIED: Net weight per set is 1000 pounds . A set of GreenTech 286 consists of one (1) 55 gallon drum of 'A' component and one (1) 55 gallon drum of 'B' component.

STORAGE: GreenTech 286 should be stored between 60° – 80° F out of direct sunlight. Do not allow material to freeze. Shelf Life for unopened containers is 6 months when stored properly.

SAFETY PRECAUTIONS: Health Considerations

This chemical system requires the use of proper safety equipment and procedures. Please follow the PolyGreen Solutions product SDS and Safety Manual for detailed information and handling guidelines.



- Consult the PolyGreen Solutions Safety Data Sheets (SDS)

For Your Protection: The information and recommendations in this publication are, to the best of our knowledge, reliable. Suggestions made concerning the products and their uses, applications, storage and handling are only the opinion of PolyGreen Solutions. Users should conduct their own tests to determine the suitability of these products for their own particular purposes and of the storage and handling methods herein suggested. The toxicity and risk characteristics of products made by PolyGreen Solutions will necessarily differ from the toxicity and risk characteristics developed when such products are used with other materials during a manufacturing process. The resulting risk characteristics should be determined and made known to ultimate end-users and processors.

Because of numerous factors affecting results, **PolyGreen Solutions makes no warranty of any kind, express or implied**, other than that the material conforms to its applicable current Standard Specifications. PolyGreen Solutions hereby disclaims any and all other warranties, including but not limited to those of merchantability or fitness for a particular purpose. No statements made herein may be construed as a representation or warranty. The liability of PolyGreen Solutions for any claims arising from or sounding in breach of warranty, negligence, strict liability, or otherwise shall be limited to the purchase price of the material.

©2019 PolyGreen Solutions, LLC. All rights reserved.

PolyGreen Solutions, LLC.
500 Sugar Mill Road; 260A
Atlanta, GA 30350
(o) 888.955.FOAM (3626)
(f) 770.481.0011
www.polygreensolutions.com

