

**Technical Data Sheet for *Polyurea Aliphatic 407*****DESCRIPTION**

PAL-407 Series is a two-component, spray-in-place flexible 100% solids aliphatic (UV color stable) polyurethane/ polyurea system. This product provides a flexible but extremely tough monolithic membrane with excellent water and chemical resistance. **PAL-407** is available in a range of property performance from flexible to rigid.

Recommended Uses

PAL-407 Series is designed for use in harsh environments where high temperature, chemical and/or abrasion resistance is required. It exhibits excellent adhesion to most materials and is suitable as a protective, abrasion/ impact liner for cementitious, wood or metal surfaces.

TYPICAL PROPERTIES

PROPERTY	TEST METHOD	COMPONENT A	COMPONENT B
Color	N/A	Light Yellow	Off-White or Black
Specific Gravity	ASTM D-1638	1.15	1.08
Viscosity	Brookfield LVF	600 cps + 100	1000 cps + 100
Mixing Ratio	By Weight	53	47
Pounds per Gallon	From Specific Gravity	9.6	8.9

PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	RESULT
Shore A/D Hardness	ASTM D-2240	*85A through 55D
UV Testing	Visual	18+ Months no white color change
Tensile Strength	ASTM D-2370	*2600-3600 psi
Abrasion Resistance (Taber)	ASTM D-4060	0.3% per 1,000 cycles
Elongation %	ASTM D-2370	*200-350%.
Tear Strength	ASTM D-1004	400 ppi Min.
Moisture Vapor Transmission, Perms	ASTM E-96	0.025 @30 Mils.

Polyurea Aliphatic 407 APPLICATION INFORMATION

Substrate Parameters

The substrate must be dry! A minimum of 5°F above the dew point is mandatory. The ambient relative humidity should not be above 85%. Pin holing may occur if the above parameters are not strictly followed. Applicator shall check initial climatic conditions. A small area shall be sprayed and check for proper application. Applicator may continue, if upon close inspection, the sprayed sample meets quality standards.

The material theoretically will cover 1,604 square feet at 100 mil dry film thickness. Coverage of the substrate should include a waste factor based on conditions at the site and type of substrate to which the material is being applied.

Spray Equipment

Spray equipment must be designed to produce a minimum of 2000 psi. The heating component of the equipment must be able to maintain a temperature at the gun of 120°F. The hose on the equipment must be heated and be rated a minimum of 2,500 psi burst pressure. The spray gun must also be rated at the pressures and throughputs required. It is recommended to agitate the Resin component for 20-30 minutes prior to application using an air or drill powered drum mixing paddle.

PRODUCT APPLICATION PARAMETERS

PROPERTY		COMPONENT A	COMPONENT B
Minimum System psi		2000 psi	2000 psi
Run Temps – Hose/Preheat		110-120F	110-120F
Gel Time		Instantaneous	Instantaneous
Total Cure		24 Hours	24 Hours
Product Working Temp.		40°F +	40°F +
Relative Humidity		MAX 85%	MAX 85%

THE INFORMATION HEREIN IS BELIEVED TO BE RELIABLE, BUT UNKNOWN RISKS MAY BE PRESENT. POLYGREEN SOLUTIONS,LLC. WARRANTS ONLY THAT THE MATERIALS SHALL BE OF MERCHANTABLE QUALITY; THIS WARRANTY IS IN LIEU OF ALL OTHER WRITTEN OR UNWRITTEN EXPRESSED OR IMPLIED WARRANTIES AND POLYGREEN SOLUTIONS,LLC EXPRESSLY DISCLAIMS ANY WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, OR FREEDOM FROM PATENT INFRINGEMENT. ACCORDINGLY, BUYER ASSUMES ALL RISKS WHATSOEVER AS TO THE USE OF THESE MATERIALS. BUYER'S EXCLUSIVE REMEDY AS TO ANY BREACH OF WARRANTY OR NEGLIGENCE CLAIM SHALL BE LIMITED TO THE PURCHASE PRICE OF THE MATERIALS. FAILURE TO STRICTLY ADHERE TO RECOMMENDED PROCEDURES SHALL RELIEVE POLYGREEN SOLUTIONS,LLC OF ALL LIABILITY WITH RESPECT TO THE MATERIALS OR THE USE THEREOF.