

PRODUCT SPECIFICATION SHEET

SETAGRIP™ TECHNOLOGY BY NUFLORS™

PRODUCT INFORMATION

CONSTRUCTION	PRODUCT	INTERNATIONAL PRODUCT SPECIFICATIONS	OVERALL THICKNESS	FACTORY FINISH	INSTALLATION
LVT - LUXURY VINYL TILE	SETAGRIP™ BY NUFLORS	ASTM F1700, CLASS III, TYPE B EMBOSSED SURFACE	4MM, 5MM, 6MM GAUGE 22MIL WEARLAYER	UV-CURED PU W/ CERAMIC BEAD	SETAGRIP™ NO ADHESIVES

PACKAGING INFORMATION

THICKNESS	TILE SIZES	TILES PER CTN / SF	SHIPPING WEIGHT PER CTN
4.0MM/22MIL	18" X 18" (457MM X457MM)	16 TILES - 36 SF (3.34SM)	45 POUNDS (20.5 KG)
	7.25" X 48" (184MM X1219MM)	15 TILES - 36 SF (3.36SM)	46 POUNDS (20.8 KG)
	9" X 48" (228MM X1219MM)	12 TILES - 36 SF (3.34SM)	47 POUNDS (21.5 KG)
5.0MM/22MIL	18" X 18" (457MM X457MM)	12 TILES - 27 SF (2.50SM)	45 POUNDS (20.5 KG)
	7.25" X 48" (184MM X1219MM)	12 TILES - 29 SF (2.68SM)	46 POUNDS (20.8 KG)
	9" X 48" (228MM X1219MM)	10 TILES - 30 SF (2.78SM)	47 POUNDS (21.5 KG)
6.0MM/22MIL	18" X 18" (457MM X457MM)	10 TILES - 22 SF (2.08SM)	45 POUNDS (19.5 KG)
	7.25" X 48" (184MM X1219MM)	10 TILES - 23 SF (2.13SM)	46 POUNDS (20.8 KG)
	9" X 48" (228MM X1219MM)	08 TILES - 24 SF (2.23SM)	46 POUNDS (20.8 KG)

PERFORMANCE SPECIFICATIONS

PRODUCT QUALIFICATIONS	ASTM F 1700	PASS
STATIC COEFFICIENT OF FRICTION	ASTM D2047	WET 0.83 / DRY 0.96
FLAME TEST - FLAME SPREAD	ASTM E648	0.45 W/CM ² OR MORE CLASS 1
FLAME TEST - SMOKE DENSITY	ASTM E662	450 OR LESS
FLEXIBILITY	ASTM F137	PASS 6MM MANDREL
THICKNESS	ASTM F386	0.157 INCH
STATIC LOAD LIMIT	ASTM F970	0.005 INCH - 250PSI
HEAT STABILITY	ASTM F1514	4.0 (SLIGHT CHANGE)
LIGHT STABILITY	ASTM F1515	4.5 (NO/SLIGHT CHANGE)
DIMENSIONAL STABILITY	ASTM F2199	LENGTH -0.003 INCH PER 12 INCHES (-0.03%)
		WIDTH -0.002 INCH PER 12 INCHES (-0.02%)
SIZE & SQUARENESS	ASTM F2421	PASS
RESISTANCE TO CHEMICAL	ASTM F925	PASS
IMPACT SOUND INSULATION	ISO 140-8:1997	DELTA IIC 20DB