



SCP DropLiner

Aromatic Polyurea Coating
Low-emitting VOC Compliant Materials

PRODUCT INFORMATION

SCP DropLiner is a fast-set, spray applied, (1:1) two component polyurea. It is 100% solids and contains zero VOCs and is designed for applications to steel and concrete. Product features include:

- ⇒ Formulated for water treatment and wastewater applications, including aeration basins, manholes, lift stations, and sewage exposure.
- ⇒ Excellent H₂S corrosion protection and resistance
- ⇒ Superior elongation which offers excellent protection against soil stress and substrate movement
- ⇒ High abrasion resistance for harsh environments
- ⇒ Seamless monolithic waterproof membrane which eliminates I&I in collection systems
- ⇒ Odorless non-toxic vapors

Color | Standard sky blue (others available upon request)

Dry Film Thickness | Standard application to concrete is between 80 and 250 mils
For applications to steel consult manufacturer

Solid's content | 100%

Gel Time / Tack Free Time | 11 seconds /
22 seconds

Packaging, storage & shelf-life | SCP DropLiner comes standard in 55 gallon drums. Other packaging is available upon request. It should be stored in sealed containers between 60F and 90F. Shelf life is 12 months in factory sealed containers.

Physical Properties & Chemical Resistance | Available upon request

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion. Minimum recommended surface preparation:

Steel | Remove all oil and grease from surface by Solvent Cleaning per SSPC-SP1. Minimum surface preparation is Near White Metal Blast Cleaning per SSPC-SP10/NACE 2. Blast clean all surfaces using a sharp, angular abrasive for optimum surface profile (3 mils / 75 microns). Prime any bare steel the same day as it is cleaned or before flash rusting occurs, as required.

Specialty Coating Products | 3370 Nacogdoches Road, Suite 128 | San Antonio, TX 78209 | Phone (210) 930-4313

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/ use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by SCP Dropline LLC.

Concrete & Masonry:

SSPC-SP13/NACE 6 or ICRI No. 310.2R-2013, CSP 3-5. Surfaces should be thoroughly clean and dry. Concrete and mortar must be cured at least 28 days @ 75°F (24°C). Remove all loose mortar and foreign material. Surface must be free of laitance, concrete dust, form release agents, moisture curing membranes, loose cement and hardeners. Fill bug holes, air pockets and other voids with recommended repair material.

Moisture content

Use calcium chloride test: 3 lb./24 hr./1,000 ft². Concrete shall be 5% maximum as per ASTM F2170 & ASTM F2420. Substrate and air temperature must be 5°F above dew point and rising before material application.

Check for soluble salts on surfaces to be coated. If amount of soluble salts exceeds recommended limits, treat accordingly. Repeat process until acceptable limits are reached. Maximum amounts of soluble salts (micrograms per square centimeter): Chlorides - 3 immersion, 7 non-immersion. Nitrates - 5 immersion, 10 non-immersion. Sulfates - 10 immersion, 20 non-immersion.

If required, holiday test in accordance with ASTM D5162 for steel, or ASTM D4787 for concrete.

APPLICATION GUIDELINES

SCP DropLiner adheres extremely well to properly prepared metal, wood, concrete, fiber glass, and other various metal surfaces.

SCP DropLiner must be applied through a two component, high pressure proportioning unit. Material and hoses should be heated to 150°F, with pressure at a minimum of 2200 psi.

Mixing Instructions

Agitate resin blend (B) component thoroughly with a drum mixer before use to disperse pigment and assure homogeneity. Do not thin. Do not agitate in air and moisture.

Consult a Technical Representative regarding specific metal/steel surface preparation and priming requirements.

ADDITIONAL INFORMATION

Safety and Handling

Please refer to MSDS for safety and handling of this material. All personnel working with this material are expected to read and understand the safety recommendations per MSDS. All personal Protection Equipment must be properly worn to protect worker health and safety.

Product User Responsibilities

Users of SCP DropLiner product are responsible for reading the general guidelines, product data sheets, specifications, and Safety Data Sheets (SDS) before using this material. Printed technical data and instructions are subject to change without notice. Contact your local SCP representative or visit our website www.scpsolutions.com for current technical data instructions.

Specialty Coating Products | 3370 Nacogdoches Road, Suite 128 | San Antonio, TX 78209 | Phone (210) 930-4313

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/ use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OF FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA, OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by SCP Droptone LLC.

Revision Date: October 8, 2025